
**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 

## City Of Mount Pearl INTERNATIONAL Flyer/Salter, 21-21D

Component Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (24 LTR)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		OF0000533		
	Sample Date		Client Info		30 May 2022		
	Machine Age	hrs	Client Info		841		
	Oil Age	hrs	Client Info		841		
	Filter Age	hrs	Client Info		153		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>90	20		
Metal levels are typical for a components first oil change.	Chromium	ppm	ASTM D5185(m)		<1		
	Nickel	ppm	ASTM D5185(m)	>2	<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		<1		
	Aluminum	ppm	ASTM D5185(m)	>20	3		
	Lead	ppm	ASTM D5185(m)	>40	4		
	Copper	ppm	ASTM D5185(m)	>330	122		
	Tin	ppm	ASTM D5185(m)	>15	<1		
	Vanadium	ppm	ASTM D5185(m)		0		
CONTAMINATION	Ciliaan		ACTM DE10E(m)	. 05			
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	8		
There is no indication of any contamination in the oil.	Potassium Fuel	ppm	ASTM D5185(m) WC Method	>3.0	2 <1.0		
	Water		WC Method		×1.0 NEG		
	Glycol		WC Method	70.2	NEG		
	Soot %	%	ASTM D7844*	>6	0		
	Nitration	Abs/cm	ASTM D7624*	>20	6.9		
	Sulfation	Abs/.1mm		>30	20.7		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>158	3		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185(m)		8		
	Barium	ppm	ASTM D5185(m)	10	1		
	Molybdenum	ppm	ASTM D5185(m)		51		
	Manganese	ppm	ASTM D5185(m)		2		
	Magnesium	ppm	ASTM D5185(m)	450	953		
	Calcium	ppm	ASTM D5185(m)	3000	1063		
	Phosphorus	ppm	ASTM D5185(m)	1150	1024		
	Zinc	ppm	ASTM D5185(m)	1350	1137		
	Sulfur	ppm	ASTM D5185(m)	4250	2595		
	Oxidation	Abs/.1mm	ASTM D7414*	>25	14.6		
	Base Number (BN)	mg KOH/g	ASTM D2896*	8.5	9.32		
	Visc @ 100°C	cSt	ASTM D7279(m)	14.4	14.3		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : OF0000533 Lab Number : 02494366 Unique Number : 5411325

Test Package : MOB 2

Received **Tested** Diagnosed

: 13 Jun 2022 : 14 Jun 2022 : 14 Jun 2022 - Wes Davis Oil Filtration Solutions Ltd.

PO BOX 16125 CONCEPTION BAY SOUTH, NL

CA A1X 2E2 Contact: BILL BUTLER

BBUTLER@OILFILTRATIONSOLUTIONS.COM

T: (709)834-8433 F: (709)834-8435

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

Submitted By: BILL BUTLER