

WEAR	
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id **ROOM #2112** Component **Gearbox** Fluid **DAVLEY DARMEX RPL-NTO140 (--- GAL)**

RECOMMENDATION

This is a baseline read-out on the submitted sample.

	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	5

WEAR

Component wear rates appear to be normal (unconfirmed).

.

Sulfur

ppm ASTM D5185(m)

CONTAMINATION

Insufficient sample was received to conduct all the routine laboratory tests.

FLUID CONDITION

{not applicable}

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		СВ		
Sample Date		Client Info		27 Jan 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
Iron	ppm	ASTM D5185(m)	>200	2		
Chromium	ppm	ASTM D5185(m)	>15	0		
Nickel	ppm	ASTM D5185(m)	>15	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	0		
Lead	ppm	ASTM D5185(m)	>100	0		
Copper	ppm	ASTM D5185(m)	>200	1		
Tin	ppm	ASTM D5185(m)	>25	0		
Vanadium	ppm	ASTM D5185(m)		0		
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Silicon	ppm	ASTM D5185(m)	>50	3		
Potassium	ppm	ASTM D5185(m)	>20	0		
Water		WC Method	>0.2	NEG		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
C a aliu una				•		
Sodium	ppm	ASTM D5185(m)		0		
Boron	ppm	ASTM D5185(m)		<1		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		0		
Calcium	ppm	ASTM D5185(m)		0		
Phosphorus	ppm	ASTM D5185(m)		185		
Zinc	ppm	ASTM D5185(m)		4		
Sulfur	nnm	ASTM DE185(m)		16		

Contact/Location: Emmanuel Okelue - APOETO Page 1 of 2

16

