



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MAXUM OL372057 (S/N MXGA09MVE900)

Component
Port Gasoline Engine

Fluid
MERCUISER 25W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0752494	---	---
Sample Date		Client Info		04 May 2023	---	---
Machine Age	hrs	Client Info		0	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Not Chngd	---	---
Filter Changed		Client Info		Not Chngd	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>150	54	---	---
Chromium	ppm	ASTM D5185(m)	>20	2	---	---
Nickel	ppm	ASTM D5185(m)	>5	<1	---	---
Titanium	ppm	ASTM D5185(m)		<1	---	---
Silver	ppm	ASTM D5185(m)	>2	0	---	---
Aluminum	ppm	ASTM D5185(m)	>40	3	---	---
Lead	ppm	ASTM D5185(m)	>50	7	---	---
Copper	ppm	ASTM D5185(m)	>155	2	---	---
Tin	ppm	ASTM D5185(m)	>10	2	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>30	12	---	---
Potassium	ppm	ASTM D5185(m)	>20	1	---	---
Fuel		WC Method	>4.0	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	ASTM D7844*		0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	7.4	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	18.2	---	---
Silt	scalar	Visual*	NONE	NONE	---	---
Debris	scalar	Visual*	NONE	NONE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*	>0.2	NEG	---	---

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>400	4	---	---
Boron	ppm	ASTM D5185(m)		33	---	---
Barium	ppm	ASTM D5185(m)		0	---	---
Molybdenum	ppm	ASTM D5185(m)		6	---	---
Manganese	ppm	ASTM D5185(m)		<1	---	---
Magnesium	ppm	ASTM D5185(m)		120	---	---
Calcium	ppm	ASTM D5185(m)		2002	---	---
Phosphorus	ppm	ASTM D5185(m)		821	---	---
Zinc	ppm	ASTM D5185(m)		843	---	---
Sulfur	ppm	ASTM D5185(m)		2386	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	11.1	---	---
Visc @ 100°C	cSt	ASTM D7279(m)		12.1	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0752494 **Received** : 09 May 2023
Lab Number : 02556169 **Tested** : 09 May 2023
Unique Number : 5577209 **Diagnosed** : 09 May 2023 - Wes Davis
Test Package : MOB 1 (Additional Tests: Visual)

FMC Marine & The Knotical Shop
 373 Barton St
 STONEY CREEK, ON
 CA L8E 2L8
 Contact: Peter Ohlhoff
 pohloff@fmcgroup.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: