WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**


Machine Id

NO UNIT CB0031461

Hydraulic System

AW HYDRAULIC OIL ISO 32 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) AW HYDRAULIC OIL ISO 32. Please confirm. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.	Sample Number		Client Info		CB0031461		
	Sample Date		Client Info		29 Jul 2023		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>20	0		
	Chromium	ppm	ASTM D5185(m)	>20	0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185(m)	>20	0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>20	0		
	Lead		ASTM D5185(m)	>20	<1		
	Copper	ppm	ASTM D5185(m)	>20	<1		
		ppm					
	Tin	ppm	ASTM D5185(m)	>20	0		
	Vanadium	ppm	ASTM D5185(m)	NONE	0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.	Silicon	ppm	ASTM D5185(m)	>15	0		
	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water		WC Method	>0.05	NEG		
	Particles >4µm		ASTM D7647	>5000	875		
	Particles >6µm		ASTM D7647	>1300	262		
	Particles >14µm		ASTM D7647		16		
	Particles >21µm		ASTM D7647		3		
	Particles >38µm		ASTM D7647		0		
	Particles >71µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		17/15/11		
	Silt	scalar	Visual*	NONE	NONE		
				NONE	VLITE		
	Debris	scalar	Visual*				
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.05	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185(m)	5	<1		
	Barium	ppm	ASTM D5185(m)	5	0		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	25	<1		
	Calcium	ppm	ASTM D5185(m)	200	40		
	Phosphorus	ppm	ASTM D5185(m)	300	358		
	Zinc	ppm	ASTM D5185(m)	370	359		
	Sulfur	ppm	ASTM D5185(m)	2500	698		
	Acid Number (AN)		ASTM D3103(III) ASTM D974*		0.37		
	Visc @ 40°C	mg KOH/g					
	VISC @ 40°C	cSt	ASTM D7279(m)	32	31.2		





ISO 17025:2017 Accredited Laboratory

 Laboratory
 : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9

 Sample No.
 : CB0031461
 Received
 : 15 Aug 2023

 Lab Number
 : 02575927
 Tested
 : 16 Aug 2023 - Wes Davis

 Unique Number
 : 5628987
 Diagnosed
 : 16 Aug 2023 - Wes Davis

Test Package : IND 2

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.