WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

SURELINE PROJECTS [SL23-089]

64002

Rear Right Final Drive

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		VCP370794		
	Sample Date		Client Info		15 Nov 2023		
	Machine Age	hrs	Client Info		502		
	Oil Age	hrs	Client Info		502		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	297		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		4		
	Nickel	ppm	ASTM D5185(m)		<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		<1		
	Aluminum	ppm	ASTM D5185(m)	>25	8		
	Lead	ppm	ASTM D5185(m)	>25	0		
	Copper	ppm	ASTM D5185(m)	>50	<1		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon		ACTM DE10E(m)	. 75	20		
	Potassium	ppm	ASTM D5185(m) ASTM D5185(m)	>75	39 2		
There is no indication of any contamination in the oil.	Water	ppiii	WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		<1		
	Barium	ppm	ASTM D5185(m)		1		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		4		
	Magnesium	ppm	ASTM D5185(m)		2		
	Calcium	ppm	ASTM D5185(m)		12		
	Phosphorus	ppm	ASTM D5185(m)		296		
	Zinc	ppm	ASTM D5185(m)		9		
	Sulfur	ppm	ASTM D5185(m)		13658		
	Visc @ 40°C	cSt	ASTM D7279(m)		171		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: VCP370794 Lab Number : 02601311 Unique Number : 5694396 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested**

: 06 Dec 2023 : 06 Dec 2023 Diagnosed

: 07 Dec 2023 - Bill Quesnel

GREAT WEST EQUIPMENT P.O. BOX 6067, 12623 CHARLIE LAKE FRONTAGE RD FORT ST. JOHN, BC CA V1J 2B0

> Contact: Mathew Stockley mstockley@gwequipmnet.com T: (250)785-4223 F: (250)785-4237

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.