



LIEBHERR

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
LIEBHERR LH50M 112359-1216
Component
Rear Differential
Fluid
PETRO CANADA TRAXON 75W90 SYNTHETIC (23 LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0269702	LH0224995	LH0221781
Sample Date		Client Info		03 Jan 2024	24 May 2023	02 Nov 2022
Machine Age	hrs	Client Info		7308	6000	5107
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>190	10	15	34
Chromium	ppm	ASTM D5185(m)	>2	0	0	0
Nickel	ppm	ASTM D5185(m)	>2	<1	<1	<1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)		0	0	0
Aluminum	ppm	ASTM D5185(m)	>5	<1	<1	<1
Lead	ppm	ASTM D5185(m)	>15	<1	0	<1
Copper	ppm	ASTM D5185(m)	>70	20	8	16
Tin	ppm	ASTM D5185(m)	>2	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
White Metal	scalar	Visual*	NONE	VLITE	NONE	VLITE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>20	2	4	4
Potassium	ppm	ASTM D5185(m)	>20	<1	2	<1
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<1	1	4
Boron	ppm	ASTM D5185(m)	328	290	261	186
Barium	ppm	ASTM D5185(m)	1	0	0	0
Molybdenum	ppm	ASTM D5185(m)		0	0	0
Manganese	ppm	ASTM D5185(m)		0	<1	1
Magnesium	ppm	ASTM D5185(m)	1	1	2	<1
Calcium	ppm	ASTM D5185(m)	7	13	22	4
Phosphorus	ppm	ASTM D5185(m)	1145	1208	1328	1607
Zinc	ppm	ASTM D5185(m)	3	20	25	12
Sulfur	ppm	ASTM D5185(m)	17909	20557	21192	23543
Visc @ 40°C	cSt	ASTM D7279(m)	99.6	105	102	108



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : LH0269702 **Received** : 08 Jan 2024
Lab Number : 02607193 **Diagnosed** : 08 Jan 2024
Unique Number : 5708279 **Diagnostician** : Kevin Marson
Test Package : MOB 1

RICHMOND STEEL
 12707 170 STREET
 EDMONTON, AB
 CA T5V 1L9
 Contact: Sandor Arguello

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T: (780)447-3391
 F: