WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

7502

Component Left Final Drive

Fluid							
{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is SAE 75W80 Tractor TDH Fluid. Please confirm the oil type and grade, and specify the brand of the oil on your next sample. Please specify the component make and model with your next sample.	Sample Number		Client Info		PC0072067		
	Sample Date		Client Info		07 Jan 2024		
	Machine Age	hrs	Client Info		5751		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	12		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>10	<1		
	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)		2		
	Lead	ppm	ASTM D5185(m)	>25	0		
	Copper	ppm	ASTM D5185(m)	>50	<1		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>75	10		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	1		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		6		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		120		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		14		
	Calcium	ppm	ASTM D5185(m)		3000		
	Phosphorus	ppm	ASTM D5185(m)		1027		
	Zinc	ppm	ASTM D5185(m)		1180		
	Sulfur	ppm	ASTM D5185(m)		3985		
	Visc @ 40°C	cSt	ASTM D7279(m)		51.0		
	Visc @ 100°C	cSt	ASTM D7279(m)		8.6		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number **Unique Number**

: PC0072067

: 5708348

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 LES ENTREPRISES MICHAUDVILLE INC. Recieved : 02607262 Diagnosed

: 08 Jan 2024 : 09 Jan 2024

Diagnostician : Wes Davis

270 RUE BRUNET MONT ST-HILAIRE, QC

CA J3H 0M6 Contact: Martin Trudel mtrudel@michaudville.com T:

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test Package : MOB 1 (Additional Tests: KV100, VI)

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

F: