

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



VOLVO L110H 631646

Component Rear Axle

{not provided} (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not	Sample Number		Client Info		VCP430089		
specified, however, a fluid match indicates that this fluid is SAE 75W80	Sample Date		Client Info		11 Jan 2024		
Tractor TDH Fluid. Please confirm the oil type and grade, and specify	Machine Age	hrs	Client Info		10909		
the brand of the oil on your next sample.	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	29		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>20	<1		
7.11 Somponon, Wear rates are normal.	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>30	2		
	Lead	ppm	ASTM D5185(m)	>50	0		
	Copper	ppm	ASTM D5185(m)	>120	<1		
	Tin	ppm	ASTM D5185(m)	>20	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>50	12		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	LIGHT		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

	Odor	scalar	visuai	NORIVIL	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	
	Sodium	ppm	ASTM D5185(m)		1	
	Boron	ppm	ASTM D5185(m)		107	
	Barium	ppm	ASTM D5185(m)		0	
	Molybdenum	ppm	ASTM D5185(m)		4	
	Manganese	ppm	ASTM D5185(m)		0	
	Magnesium	ppm	ASTM D5185(m)		55	
	Calcium	ppm	ASTM D5185(m)		3876	
	Phosphorus	ppm	ASTM D5185(m)		1306	
	Zinc	ppm	ASTM D5185(m)		1536	
	Sulfur	ppm	ASTM D5185(m)		3898	
	Visc @ 40°C	cSt	ASTM D7279(m)		44.9	
			- ' /			





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number **Unique Number**

Test Package : MOB 1

: VCP430089

: 02608791 : 5709877

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Recieved : 15 Jan 2024 Diagnosed : 15 Jan 2024 Diagnostician

: Wes Davis

REDHEAD EQUIPMENT LTD. HIGHWAY 16 NORTH BOX 9191 SASKATOON, SK CA S7K 7E8

Contact: Mike Derenoski

mike.derenoski@redheadequipment.ca

T: (306)651-5726 F: (306)934-4490

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.