



# LIEBHERR

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**LIEBHERR LH30M 139284-1253**  
Component  
**Front Differential**  
Fluid  
**LIEBHERR GEAR BASIC 90 LS (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LH0241869</b>	LH0239950	LH0241857
Sample Date		Client Info		<b>31 Oct 2023</b>	04 Sep 2023	07 Jun 2023
Machine Age	hrs	Client Info		<b>2739</b>	2265	1668
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>None</b>	None	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>190	<b>4</b>	5	6
Chromium	ppm	ASTM D5185(m)	>2	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m)	>2	<b>&lt;1</b>	<1	<1
Titanium	ppm	ASTM D5185(m)		<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)		<b>0</b>	<1	0
Aluminum	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	0	<1
Lead	ppm	ASTM D5185(m)	>15	<b>0</b>	<1	0
Copper	ppm	ASTM D5185(m)	>70	<b>&lt;1</b>	<1	<1
Tin	ppm	ASTM D5185(m)	>2	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	0	0
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>20	<b>&lt;1</b>	<1	2
Potassium	ppm	ASTM D5185(m)	>20	<b>0</b>	0	0
Water		WC Method	>.2	<b>NEG</b>	NEG	NEG
Silt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	Visual*	NONE	<b>NONE</b>	NONE	VLITE
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>.2	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<b>&lt;1</b>	1	1
Boron	ppm	ASTM D5185(m)	0	<b>&lt;1</b>	2	7
Barium	ppm	ASTM D5185(m)	0	<b>0</b>	<1	0
Molybdenum	ppm	ASTM D5185(m)	0	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)	0	<b>0</b>	0	<1
Magnesium	ppm	ASTM D5185(m)	<1	<b>&lt;1</b>	0	1
Calcium	ppm	ASTM D5185(m)	<1	<b>5</b>	8	20
Phosphorus	ppm	ASTM D5185(m)	2143	<b>2267</b>	2290	2391
Zinc	ppm	ASTM D5185(m)	<1	<b>4</b>	6	10
Sulfur	ppm	ASTM D5185(m)	23468	<b>25511</b>	26442	25971
Visc @ 40°C	cSt	ASTM D7279(m)	170	<b>180</b>	179	188



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : LH0241869 **Received** : 16 Jan 2024  
**Lab Number** : 02609112 **Diagnosed** : 16 Jan 2024  
**Unique Number** : 5710198 **Diagnostician** : Kevin Marson  
**Test Package** : MOBCE ( Additional Tests: Visual )

**HUBERT & FILS**  
 474 ROUTE 105  
 BOIS-FRANC, QC  
 CA J9E 3A9  
 Contact: Eric Brisebois  
 ericbrisebois99@gmail.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

T:  
F: