



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

Locomotives

Machine Id

2006

Component

Railway diesel

Fluid

RAILWAY ENGINE OIL SAE 40 (243 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please contact your representative for information regarding the proper sampling kits for your service. NOTE: We recommend using MOB 3 test kits, this testkit includes Analytical Ferrography which provides a detailed morphological analysis of wear particles present in the fluid. this testkit includes BN to determine the suitability of the oil for continued use.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0866409	WC0866404	WC0874995
Sample Date		Client Info		12 Jan 2024	04 Jan 2024	29 Dec 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Component wear rates appear to be normal (unconfirmed).

Iron	ppm	ASTM D5185(m)	>42	28	29	28
Chromium	ppm	ASTM D5185(m)	>6	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>2	<1	<1	<1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>5	0	0	0
Aluminum	ppm	ASTM D5185(m)	>4	4	4	4
Lead	ppm	ASTM D5185(m)	>30	2	2	2
Copper	ppm	ASTM D5185(m)	>95	9	10	9
Tin	ppm	ASTM D5185(m)	>10	<1	1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>22	5	5	5
Potassium	ppm	ASTM D5185(m)	>20	4	6	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*		0.8	0.8	0.8
Nitration	Abs/cm	ASTM D7624*	>20	12.8	13.1	12.7
Sulfation	Abs/.1mm	ASTM D7415*	>30	16.4	16.6	16.2
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service (unconfirmed).

Sodium	ppm	ASTM D5185(m)		8	4	4
Boron	ppm	ASTM D5185(m)	10	1	<1	<1
Barium	ppm	ASTM D5185(m)	10	0	0	0
Molybdenum	ppm	ASTM D5185(m)	25	0	0	0
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)	20	17	17	17
Calcium	ppm	ASTM D5185(m)	4500	4853	4797	4722
Phosphorus	ppm	ASTM D5185(m)	10	2	2	2
Zinc	ppm	ASTM D5185(m)	10	4	4	4
Sulfur	ppm	ASTM D5185(m)	5000	3281	3258	3326
Oxidation	Abs/.1mm	ASTM D7414*	>25	10.0	10.3	9.8
Visc @ 100°C	cSt	ASTM D7279(m)	14.4	15.2	15.3	15.3



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Vale - Transportation (Mobile Equipment)
Sample No. : WC0866409 **Received** : 19 Jan 2024
Lab Number : 02609951 **Diagnosed** : 19 Jan 2024
Unique Number : 5711037 **Diagnostician** : Kevin Marson
Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Transportation Department, (Services - Mobile Equipment)
 COPPER CLIFF, ON
 CA P0M 1N0
 Contact: Richard Rochon
 richard.rochon@vale.com
 T: (705)682-6014
 F: