



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
150
Component
Rear Transmission (Auto)
Fluid
CASTROL TRANSYND (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0889092	WC0866437	WC0816375
Sample Date		Client Info		10 Jan 2024	23 Nov 2023	25 Sep 2023
Machine Age	kms	Client Info		0	0	0
Oil Age	kms	Client Info		45459	36736	27722
Filter Age	kms	Client Info		45459	36736	27722
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184*	>105	0	---	0
Iron	ppm	ASTM D5185(m)	>230	55	46	39
Chromium	ppm	ASTM D5185(m)	>2	0	0	0
Nickel	ppm	ASTM D5185(m)	>5	<1	<1	0
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>5	0	<1	<1
Aluminum	ppm	ASTM D5185(m)	>65	10	8	7
Lead	ppm	ASTM D5185(m)	>55	3	2	2
Copper	ppm	ASTM D5185(m)	>85	7	6	5
Tin	ppm	ASTM D5185(m)	>5	<1	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the fluid.

Silicon	ppm	ASTM D5185(m)	>20	8	6	5
Potassium	ppm	ASTM D5185(m)	>20	2	<1	<1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.

Sodium	ppm	ASTM D5185(m)		5	5	5
Boron	ppm	ASTM D5185(m)	150	87	91	88
Barium	ppm	ASTM D5185(m)	0	0	0	<1
Molybdenum	ppm	ASTM D5185(m)	0	0	0	0
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)	0	1	1	<1
Calcium	ppm	ASTM D5185(m)	40	129	129	127
Phosphorus	ppm	ASTM D5185(m)	320	287	286	281
Zinc	ppm	ASTM D5185(m)	5	5	6	6
Sulfur	ppm	ASTM D5185(m)	1050	1765	1656	1643
Acid Number (AN)	mg KOH/g	ASTM D974*	1.0	1.27	---	1.48
Visc @ 40°C	cSt	ASTM D7279(m)	38.9	33.5	33.5	33.6
Visc @ 100°C	cSt	ASTM D7279(m)	7.3	6.6	6.6	6.6
Viscosity Index (VI)	Scale	ASTM D2270*	168	156	156	155



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0889092
Lab Number : 02610000
Unique Number : 5711086
Test Package : MOB 2 (Additional Tests: KV100, PQ, VI)

CITY OF THUNDER BAY
 AUTO MAINTENANCE STORES, 570 FORT WILLIAM ROAD
 THUNDER BAY, ON
 CA P7B 2Z8
 Contact: Sean Malcolm
 sean.malcolm@thunderbay.ca
 T: (807)684-2716
 F: (807)344-0237

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.