



LIEBHERR

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
LIEBHERR PR776 24302DUOCONE
Component
Unknown Component
Fluid
PETRO CANADA HYDREX AW 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0265123	---	---
Sample Date		Client Info		18 Jan 2024	---	---
Machine Age	hrs	Client Info		6158	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		N/A	---	---
Filter Changed		Client Info		N/A	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)		68	---	---
Chromium	ppm	ASTM D5185(m)		1	---	---
Nickel	ppm	ASTM D5185(m)		2	---	---
Titanium	ppm	ASTM D5185(m)		0	---	---
Silver	ppm	ASTM D5185(m)		0	---	---
Aluminum	ppm	ASTM D5185(m)		8	---	---
Lead	ppm	ASTM D5185(m)		0	---	---
Copper	ppm	ASTM D5185(m)		<1	---	---
Tin	ppm	ASTM D5185(m)		0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---

CONTAMINATION










There is no indication of any contamination in the sample.

Silicon	ppm	ASTM D5185(m)		27	---	---
Potassium	ppm	ASTM D5185(m)	>20	3	---	---
Water		WC Method		NEG	---	---
Silt	scalar	Visual*	NONE	VLITE	---	---
Debris	scalar	Visual*	NONE	NONE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*		NEG	---	---

FLUID CONDITION

The condition of the sample is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		2	---	---
Boron	ppm	ASTM D5185(m)	0	<1	---	---
Barium	ppm	ASTM D5185(m)	0	0	---	---
Molybdenum	ppm	ASTM D5185(m)	0	0	---	---
Manganese	ppm	ASTM D5185(m)	0	0	---	---
Magnesium	ppm	ASTM D5185(m)	0	3	---	---
Calcium	ppm	ASTM D5185(m)	50	73	---	---
Phosphorus	ppm	ASTM D5185(m)	330	420	---	---
Zinc	ppm	ASTM D5185(m)	430	539	---	---
Sulfur	ppm	ASTM D5185(m)	760	1883	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	46.4	41.1	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : LH0265123 **Received** : 19 Jan 2024
Lab Number : 02610010 **Diagnosed** : 19 Jan 2024
Unique Number : 5711096 **Diagnostician** : Kevin Marson
Test Package : MOB 1

ARGONAUT GOLD
 DUBREUILVILLE MINE
 DUBREUILVILLE, ON
 CA
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: