



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1826
Component
Rear Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0895810	WC0873845	WC0858490
Sample Date		Client Info		17 Jan 2024	23 Nov 2023	29 Sep 2023
Machine Age	hrs	Client Info		21128	20585	19999
Oil Age	hrs	Client Info		543	586	523
Filter Age	hrs	Client Info		543	0	523
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>100	9	10	11
Chromium	ppm	ASTM D5185(m)	>20	<1	0	0
Nickel	ppm	ASTM D5185(m)	>4	<1	<1	0
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>3	0	<1	<1
Aluminum	ppm	ASTM D5185(m)	>20	2	1	1
Lead	ppm	ASTM D5185(m)	>40	0	0	0
Copper	ppm	ASTM D5185(m)	>330	1	2	1
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	3	3	4
Potassium	ppm	ASTM D5185(m)	>20	<1	0	0
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0.3	0.3	0.4
Nitration	Abs/cm	ASTM D7624*	>20	8.7	9.1	9.5
Sulfation	Abs/.1mm	ASTM D7415*	>30	21.6	24.1	25.4
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>158	<1	1	2
Boron	ppm	ASTM D5185(m)	250	2	2	2
Barium	ppm	ASTM D5185(m)	10	0	<1	<1
Molybdenum	ppm	ASTM D5185(m)	100	59	58	59
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)	450	950	932	946
Calcium	ppm	ASTM D5185(m)	3000	1047	1017	1037
Phosphorus	ppm	ASTM D5185(m)	1150	987	908	968
Zinc	ppm	ASTM D5185(m)	1350	1173	1149	1174
Sulfur	ppm	ASTM D5185(m)	4250	2675	2452	2496
Oxidation	Abs/.1mm	ASTM D7414*	>25	19.8	25.5	27.3
Visc @ 100°C	cSt	ASTM D7279(m)	14.4	13.8	13.6	13.5



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0895810 **Received** : 22 Jan 2024
Lab Number : 02610128 **Diagnosed** : 22 Jan 2024
Unique Number : 5711214 **Diagnostician** : Wes Davis
Test Package : MOB 1

KINGSTON TRANSIT
 1181 JOHN COUNTER BLVD
 KINGSTON, ON
 CA K7K 6C7
 Contact: Brent Gunter
 bgunter@cityofkingston.ca
 T: (613)546-4291
 F: (613)542-1504

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.