



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[83856]
 Machine Id
330 MAIN ST MILTON BELL 36089-1-1-0613
 Component
Rear Diesel Engine
 Fluid
ESSO XD-3 EXTRA 15W40 (60 LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PN0005636	PN0002297	PN0308276
Sample Date		Client Info		17 Jan 2024	22 Feb 2021	31 Jan 2019
Machine Age	hrs	Client Info		227	163	112
Oil Age	hrs	Client Info		20	0	30
Filter Age	hrs	Client Info		20	0	30
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>100	1	2	2
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>4	<1	<1	0
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>3	0	0	2
Aluminum	ppm	ASTM D5185(m)	>20	2	2	<1
Lead	ppm	ASTM D5185(m)	>40	<1	<1	<1
Copper	ppm	ASTM D5185(m)	>330	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	2	7	8
Potassium	ppm	ASTM D5185(m)	>20	<1	10	0
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0	0	0
Nitration	Abs/cm	ASTM D7624*	>20	6.9	5.6	4.8
Sulfation	Abs/.1mm	ASTM D7415*	>30	16.8	20.5	21.8
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>192	1	3	2
Boron	ppm	ASTM D5185(m)		75	63	63
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		23	48	37
Manganese	ppm	ASTM D5185(m)		0	<1	<1
Magnesium	ppm	ASTM D5185(m)		49	351	450
Calcium	ppm	ASTM D5185(m)	3780	2113	1723	1618
Phosphorus	ppm	ASTM D5185(m)	1370	993	783	737
Zinc	ppm	ASTM D5185(m)	1500	1089	964	845
Sulfur	ppm	ASTM D5185(m)	3800	3469	2551	2165
Oxidation	Abs/.1mm	ASTM D7414*	>25	12.3	16.7	19.2
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	14.2	13.5	13.5



ISO 17025:2017
Accredited
Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PN0005636 **Received** : 24 Jan 2024
Lab Number : 02610860 **Diagnosed** : 24 Jan 2024
Unique Number : 5719955 **Diagnostician** : Wes Davis
Test Package : MOB 1

POWER STATION INC.
 1050 JAYSON COURT
 MISSISSAUGA, ON
 CA L4W 2V5
 Contact: Brett Kinkley
 Bkinkley@pwrstn.com
 T:
 F: (905)665-8544

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.