WEAR CONTAMINATION FLUID CONDITION

Current

History1

History2

Limit/Abn

NORMAL NORMAL NORMAL



RECOMMENDATION

LIEBHERR LH60M 155308

Component Rear Right Wheel Hub

GEAR OIL SAE 75W90 (--- GAL)

Resample at the next service interval to monitor. The fluid was not	Sample Number		Client Info		LH0285038	
specified, however, a fluid match indicates that this fluid is (GENERIC)	Sample Date		Client Info		02 Feb 2024	
GEAR OIL SAE 75W90. Please confirm.	Machine Age	hrs	Client Info		474	
	Oil Age	hrs	Client Info		0	
	Filter Age	hrs	Client Info		0	
	Oil Changed		Client Info		Changed	
	Filter Changed		Client Info		N/A	
	Sample Status				NORMAL	
WEAR	Iron		ASTM D5185(m)	>650	14	
WLAIT	Chromium	ppm	ASTM D5185(III) ASTM D5185(m)			
All component wear rates are normal.	Nickel	ppm	(/		0	
	Titanium	ppm	ASTM D5185(m)		0	
	Silver	ppm	ASTM D5185(m)	>4		
		ppm	ASTM D5185(m)	05	0	
	Aluminum	ppm	ASTM D5185(m)		<1	
	Lead	ppm	ASTM D5185(m)		<1	
	Copper	ppm	ASTM D5185(m)		4	
	Tin	ppm	ASTM D5185(m)	>4	0	
	Vanadium	ppm	ASTM D5185(m)	NONE	0	
	White Metal	scalar	Visual*	NONE	VLITE	
	Yellow Metal	scalar	Visual*	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>75	6	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	<1	
There is no malecular of any containing of in the on.	Water		WC Method	>0.2	NEG	
	Silt	scalar	Visual*	NONE	NONE	
	Debris	scalar	Visual*	NONE	NONE	

Sand/Dirt

Appearance

scalar

scalar Visual*

Visual*

Test

UOM

Method

FLUID CONDITION

The condition of the oil is acceptable for the time in service.


Odor	scalar	Visual*	NORML	NORML	
Emulsified Water	scalar	Visual*	>0.2	NEG	
Sodium	ppm	ASTM D5185(m)		4	
Boron	ppm	ASTM D5185(m)	400	136	
Barium	ppm	ASTM D5185(m)	200	2	
Molybdenum	ppm	ASTM D5185(m)	12	0	
Manganese	ppm	ASTM D5185(m)		0	
Magnesium	ppm	ASTM D5185(m)	12	1	
Calcium	ppm	ASTM D5185(m)	150	6	
Phosphorus	ppm	ASTM D5185(m)	1650	1809	
Zinc	ppm	ASTM D5185(m)	125	10	
Sulfur	ppm	ASTM D5185(m)	22500	29130	
Visc @ 40°C	cSt	ASTM D7279(m)	109	137	

NONE

NORML

NONE

NORML





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: LH0285038 Lab Number : 02616391 Unique Number : 5733501 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 16 Feb 2024 **Tested**

Diagnosed

: 16 Feb 2024 : 16 Feb 2024 - Wes Davis

CA L1N 5T1 Contact: Tyson Young tyoung@gerdauameristeel.com

GERDAU AMERISTEEL

1 GERDAU COURT

WHITBY, ON

T: (905)668-8811 F: (905)668-6469

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.