WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



LIEBHERR LH60M 155308

Rear Axle GEAR OIL SAE 75W90 (GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm.	Sample Number		Client Info		LH0285042		
	Sample Date		Client Info		02 Feb 2024		
	Machine Age	hrs	Client Info		474		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	11		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>25	<1		
	Lead	ppm	ASTM D5185(m)	>25	<1		
	Copper	ppm	ASTM D5185(m)	>50	5		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>75	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		4		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	134		
	Barium	ppm	ASTM D5185(m)	200	2		
	Molybdenum	ppm	ASTM D5185(m)	12	0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	12	<1		
	Calcium	ppm	ASTM D5185(m)	150	6		
	Phosphorus	ppm	ASTM D5185(m)	1650	1785		
	Zinc	ppm	ASTM D5185(m)	125	10		
	Sulfur	ppm	ASTM D5185(m)	22500	29209		
	Visc @ 40°C	cSt	ASTM D7279(m)	109	137		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: LH0285042 Lab Number : 02616395 Unique Number : 5733505

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : 16 Feb 2024 Received **Tested** : 16 Feb 2024 - Wes Davis

: 16 Feb 2024

Diagnosed Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

GERDAU AMERISTEEL

1 GERDAU COURT WHITBY, ON CA L1N 5T1

Contact: Tyson Young tyoung@gerdauameristeel.com

T: (905)668-8811 F: (905)668-6469