

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id LIEBHERR LH60M 155308 Component Swing Drive Fluid SAE 75W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0285044		
Sample Date		Client Info		02 Feb 2024		
Machine Age	hrs	Client Info		474		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
Iron	ppm	ASTM D5185(m)	>350	118		
Chromium	ppm	ASTM D5185(m)	>15	<1		
Nickel	ppm	ASTM D5185(m)	>5	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>5	2		
Lead	ppm	ASTM D5185(m)	>10	2		
Copper	ppm	ASTM D5185(m)	>300	59		
Tin	ppm	ASTM D5185(m)	>15	4		
Vanadium	ppm	ASTM D5185(m)		0		
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	VLITE		
Silicon			>15	9		
Potassium	ppm	ASTM D5185(m) ASTM D5185(m)	>20	9		
Water	ppm	WC Method	>20	NEG		
Silt	scalar	Visual*	>0.2	VLITE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water		Visual*				
	scalar	VISUAI	>0.2	NEG		
Sodium	ppm	ASTM D5185(m)		2		
Boron	ppm	ASTM D5185(m)	150	4		
Barium	ppm	ASTM D5185(m)	5	5		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)	0	1		
Calcium	ppm	ASTM D5185(m)	20	43		
Phosphorus	ppm	ASTM D5185(m)	1200	2265		
Zinc	ppm	ASTM D5185(m)	25	16		
Sulfur	ppm	ASTM D5185(m)	22000	24482		
N/ 0 4000	01		00 F	101		

Visc @ 40°C

cSt

ASTM D7279(m) 99.5

Contact/Location: Tyson Young - LAKWHI

181



