



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**NO UNIT PC0057136**  
Component  
**Diesel Engine**  
Fluid  
**CASTROL MHP 153 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PC0057136</b>	---	---
Sample Date		Client Info		<b>05 Feb 2024</b>	---	---
Machine Age	hrs	Client Info		<b>3994</b>	---	---
Oil Age	hrs	Client Info		<b>289</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>N/A</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>100	<b>6</b>	---	---
Chromium	ppm	ASTM D5185(m)	>20	<b>0</b>	---	---
Nickel	ppm	ASTM D5185(m)	>4	<b>0</b>	---	---
Titanium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Silver	ppm	ASTM D5185(m)	>3	<b>0</b>	---	---
Aluminum	ppm	ASTM D5185(m)	>20	<b>2</b>	---	---
Lead	ppm	ASTM D5185(m)	>40	<b>3</b>	---	---
Copper	ppm	ASTM D5185(m)	>330	<b>8</b>	---	---
Tin	ppm	ASTM D5185(m)	>15	<b>1</b>	---	---
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	---	---

## CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	<b>5</b>	---	---
Potassium	ppm	ASTM D5185(m)	>20	<b>&lt;1</b>	---	---
Fuel		WC Method	>5	<b>&lt;1.0</b>	---	---
Water		WC Method	>0.2	<b>NEG</b>	---	---
Glycol		WC Method		<b>NEG</b>	---	---
Soot %	%	ASTM D7844*	>3	<b>0</b>	---	---
Nitration	Abs/cm	ASTM D7624*	>20	<b>7.3</b>	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	<b>13.2</b>	---	---
Emulsified Water	scalar	Visual*	>0.2	<b>NEG</b>	---	---

## FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Boron	ppm	ASTM D5185(m)		<b>5</b>	---	---
Barium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Molybdenum	ppm	ASTM D5185(m)		<b>0</b>	---	---
Manganese	ppm	ASTM D5185(m)		<b>0</b>	---	---
Magnesium	ppm	ASTM D5185(m)		<b>16</b>	---	---
Calcium	ppm	ASTM D5185(m)		<b>5296</b>	---	---
Phosphorus	ppm	ASTM D5185(m)		<b>904</b>	---	---
Zinc	ppm	ASTM D5185(m)		<b>958</b>	---	---
Sulfur	ppm	ASTM D5185(m)		<b>9761</b>	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	<b>6.4</b>	---	---
Visc @ 40°C	cSt	ASTM D7279(m)		<b>83.2</b>	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	11.5	<b>10.2</b>	---	---
Viscosity Index (VI)	Scale	ASTM D2270*		<b>103</b>	---	---



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : PC0057136 **Received** : 20 Feb 2024  
**Lab Number** : 02616627 **Tested** : 20 Feb 2024  
**Unique Number** : 5733737 **Diagnosed** : 20 Feb 2024 - Wes Davis  
**Test Package** : MOB 1 ( Additional Tests: KV40, VI )

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

**THUNDER BAY TUG**  
 600-100 MAIN ST  
 THUNDER BAY, ON  
 CA P7B 6R9  
 Contact: Service Manager  
 nate.daws86@gmail.com

T:  
F: