



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 644K LDR009
Component
Diesel Engine
Fluid
MOBIL 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0904238	WC0886091	WC0865541
Sample Date		Client Info		10 Feb 2024	05 Jan 2024	07 Nov 2023
Machine Age	hrs	Client Info		12116	111363	11055
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>51	33	36	39
Chromium	ppm	ASTM D5185(m)	>11	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	2	2	4
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>3	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>31	2	2	3
Lead	ppm	ASTM D5185(m)	>26	<1	<1	<1
Copper	ppm	ASTM D5185(m)	>26	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>4	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>22	5	7	4
Potassium	ppm	ASTM D5185(m)	>20	1	4	3
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0.2	0.3	0.4
Nitration	Abs/cm	ASTM D7624*	>20	6.7	7.3	7.4
Sulfation	Abs/.1mm	ASTM D7415*	>30	21.6	22.0	20.8
Emulsified Water	scalar	Visual*	>0.21	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>118	2	2	2
Boron	ppm	ASTM D5185(m)		35	35	43
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		40	42	35
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)		529	571	463
Calcium	ppm	ASTM D5185(m)		1691	1619	1749
Phosphorus	ppm	ASTM D5185(m)		767	820	844
Zinc	ppm	ASTM D5185(m)		878	930	1022
Sulfur	ppm	ASTM D5185(m)		2264	2341	2412
Oxidation	Abs/.1mm	ASTM D7414*	>25	20.2	19.6	17.4
Visc @ 100°C	cSt	ASTM D7279(m)		13.3	13.3	13.3



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0904238
Lab Number : 02616952
Unique Number : 5734062
Test Package : MOB 1
Received : 21 Feb 2024
Tested : 22 Feb 2024
Diagnosed : 22 Feb 2024 - Wes Davis

Agnico Eagle Canada
 1350 Government Rd. W, MACASSA COMPLEX
 Kirkland Lake, ON
 CA P2N 3J1
 Contact: Jay Gould
 MacassaMobileUGPlanning@agnicoeagle.com
 T: (705)567-5208
 F: (705)567-5221

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.