



LIEBHERR

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	MARGINAL
FLUID CONDITION	NORMAL



Machine Id
LIEBHERR LH40M 156305-1215
Component
Diesel Engine
Fluid
{not provided} (--- GAL)

RECOMMENDATION

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. No other corrective action is recommended at this time. The fluid was not specified, however, a fluid match indicates that this fluid is SAE 30 Diesel Engine Oil. Please confirm the oil type and grade, and specify the brand of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0278468	---	---
Sample Date		Client Info		20 Feb 2024	---	---
Machine Age	hrs	Client Info		536	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				MARGINAL	---	---

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>100	10	---	---
Chromium	ppm	ASTM D5185(m)	>5	1	---	---
Nickel	ppm	ASTM D5185(m)	>5	<1	---	---
Titanium	ppm	ASTM D5185(m)		0	---	---
Silver	ppm	ASTM D5185(m)	>3	0	---	---
Aluminum	ppm	ASTM D5185(m)	>15	2	---	---
Lead	ppm	ASTM D5185(m)	>30	6	---	---
Copper	ppm	ASTM D5185(m)	>125	95	---	---
Tin	ppm	ASTM D5185(m)	>5	<1	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---

CONTAMINATION











Light fuel dilution occurring. No other contaminants were detected in the oil.

Silicon	ppm	ASTM D5185(m)	>60	7	---	---
Potassium	ppm	ASTM D5185(m)	>20	3	---	---
Fuel	%	ASTM D7593*	>5	▲ 2	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	ASTM D7844*	>3	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	12.6	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	40.3	---	---
Emulsified Water	scalar	Visual*	>0.2	NEG	---	---

FLUID CONDITION

Viscosity of sample indicates oil is within SAE 30 range, advise investigate. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		2	---	---
Boron	ppm	ASTM D5185(m)		100	---	---
Barium	ppm	ASTM D5185(m)		29	---	---
Molybdenum	ppm	ASTM D5185(m)		46	---	---
Manganese	ppm	ASTM D5185(m)		<1	---	---
Magnesium	ppm	ASTM D5185(m)		910	---	---
Calcium	ppm	ASTM D5185(m)		1355	---	---
Phosphorus	ppm	ASTM D5185(m)		671	---	---
Zinc	ppm	ASTM D5185(m)		780	---	---
Sulfur	ppm	ASTM D5185(m)		1975	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	53.0	---	---
Visc @ 100°C	cSt	ASTM D7279(m)		11.8	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : LH0278468 **Received** : 22 Feb 2024
Lab Number : 02617374 **Tested** : 23 Feb 2024
Unique Number : 5734484 **Diagnosed** : 23 Feb 2024 - Kevin Marson
Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel)

Urban Mine
 72 Rothwell Rd.
 Winnipeg, MB
 CA R3P 2H7
 Contact: SERVICE

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T: (204)774-0192
 F: