WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL




Area (374940)

LIEBHERR LH30M 137944-1253

Swing Drive

Swing Drive GEAR OIL SAE 75W90 (GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm.	Sample Number		Client Info		LH0278729	LH0216022	
	Sample Date		Client Info		22 Feb 2024	31 Aug 2022	
	Machine Age	hrs	Client Info		2777	551	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185(m)	>1450	100	115	
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>11	<1	<1	
	Nickel	ppm	ASTM D5185(m)	>3	0	0	
	Titanium	ppm	ASTM D5185(m)		0	0	
	Silver	ppm	ASTM D5185(m)		0	0	
	Aluminum	ppm	ASTM D5185(m)	>4	<1	<1	
	Lead	ppm	ASTM D5185(m)	>4	2	2	
	Copper	ppm	ASTM D5185(m)	>542	63	51	
	Tin	ppm	ASTM D5185(m)	>38	2	4	
	Vanadium	ppm	ASTM D5185(m)		0	0	
	White Metal	scalar	Visual*	NONE	NONE	NONE	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>15	2	3	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	1	2	
	Water	1-1-	WC Method	>0.2	NEG	NEG	
	Silt	scalar	Visual*	NONE	NONE	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		2	6	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	236	8	
	Barium	ppm	ASTM D5185(m)	200	4	10	
	Molybdenum	ppm	ASTM D5185(m)	12	0	0	
	Manganese	ppm	ASTM D5185(m)		<1	2	
	Magnesium	ppm	ASTM D5185(m)	12	3	2	
	Calcium	ppm	ASTM D5185(m)	150	17	28	
	Phosphorus	ppm	ASTM D5185(m)	1650	1383	2227	
	Zinc	ppm	ASTM D5185(m)	125	20	37	
	Sulfur	ppm	ASTM D5185(m)	22500	21937	31697	
	Visc @ 40°C	cSt	ASTM D7279(m)	109	105	178	





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02617723 Unique Number : 5734833

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : LH0278729 **Tested**

Diagnosed

Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

: 23 Feb 2024

: 23 Feb 2024

: 23 Feb 2024 - Wes Davis

KINGS AUTO WRECKERS

1866 DRUMMOND LINE PETERBOROUGH, ON CA K9J 6X8

Contact: Service Manager

T: F: