

Area
MICHAUDVILLE
Machine Id
1208
Component
Transmission (Auto)
Fluid
DEXRON III (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DEXRON III. Please confirm.
Please specify the component make and model with your next sample.

WEAR

All component wear rates are normal.











CONTAMINATION

There is no indication of any contamination in the fluid.

FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PC0084407	PC0082569	PC0075868
Sample Date		Client Info		28 Feb 2024	24 Oct 2023	10 Oct 2023
Machine Age	hrs	Client Info		13650	13147	17362
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL
Iron	ppm	ASTM D5185(m)	>160	14	8	▲ 179
Chromium	ppm	ASTM D5185(m)	>5	0	0	0
Nickel	ppm	ASTM D5185(m)	>5	<1	0	0
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>5	0	<1	<1
Aluminum	ppm	ASTM D5185(m)	>50	4	3	29
Lead	ppm	ASTM D5185(m)	>50	2	1	14
Copper	ppm	ASTM D5185(m)	>225	3	2	41
Tin	ppm	ASTM D5185(m)	>10	<1	0	2
Vanadium	ppm	ASTM D5185(m)		0	0	0
White Metal	scalar	Visual*	NONE	NONE	NONE	VLITE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Silicon	ppm	ASTM D5185(m)	>20	10	8	10
Potassium	ppm	ASTM D5185(m)	>20	<1	0	<1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	.2%	NEG
Sodium	ppm	ASTM D5185(m)		2	2	6
Boron	ppm	ASTM D5185(m)		81	82	144
Barium	ppm	ASTM D5185(m)		0	<1	<1
Molybdenum	ppm	ASTM D5185(m)		0	<1	0
Manganese	ppm	ASTM D5185(m)		0	0	1
Magnesium	ppm	ASTM D5185(m)		3	2	1
Calcium	ppm	ASTM D5185(m)		107	104	82
Phosphorus	ppm	ASTM D5185(m)		228	217	357
Zinc	ppm	ASTM D5185(m)		10	9	5
Sulfur	ppm	ASTM D5185(m)		1585	1479	1389
Visc @ 40°C	cSt	ASTM D7279(m)	26.0	33.4	34.1	35.1
Visc @ 100°C	cSt	ASTM D7279(m)	5.5	6.6	6.8	7
Viscosity Index (VI)	Scale	ASTM D2270*	155	157	162	165



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0084407
Lab Number : 02618987
Unique Number : 5736097
Test Package : MOB 1 (Additional Tests: KV100, VI)

LES ENTREPRISES MICHAUVILLE INC.
 270 RUE BRUNET
 MONT ST-HILAIRE, QC
 CA J3H 0M6
 Contact: Martin Trudel
 mtrudel@michaudville.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: