

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



LIEBHERR LB35 115696

Distribution Gear

Distribution Gear							
{not provided} (LTR)	- .						
RECOMMENDATION Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		LH0270535 29 Feb 2024		
	Sample Date	hrs	Client Info		29 Feb 2024 2999		
	Machine Age		Client Info				
	Oil Age	hrs			0		
	Filter Age Oil Changed	hrs	Client Info		0 Changed		
	Filter Changed		Client Info		N/A		
	Sample Status		Chefft iiilo		NORMAL		
<u> </u>	Sample Status						
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185(m)	>300	13		
	Chromium	ppm	ASTM D5185(m)	>3	0		
	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>5	<1		
	Lead	ppm	ASTM D5185(m)	>60	0		
	Copper	ppm	ASTM D5185(m)	>35	6		
	Tin	ppm	ASTM D5185(m)	>5	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	<1		
	Potassium	ppm	ASTM D5185(m)		<1		
There is no indication of any contamination in the oil.	Water	ррпп	WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		263		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		1 -		
	Calcium	ppm	ASTM D5185(m)		5		
	Phosphorus	ppm	ASTM D5185(m)		1273		
	Zinc	ppm	ASTM D5185(m)		12		
	Sulfur	ppm	ASTM D5185(m)		21054		
	Visc @ 40°C	cSt	ASTM D7279(m)		102		
Report Id: ASTSCA [WCAMIS] 02619654 (Generated: 03/04/2024 14:44:35) Rev: 1			C	antact/L	ocation: Son	ADDRACT// ADD	r - ASTSCA





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : LH0270535 Lab Number : 02619654 Unique Number : 5736764 Test Package : MOB 1

Received **Tested**

: 04 Mar 2024 : 04 Mar 2024

Diagnosed : 04 Mar 2024 - Wes Davis

ASTRO SHORING 645 CORONATION DRIVE SCARBOROUGH, ON CA M1E 2K4

Contact: Service Manager

T:

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Contact/Location: Service Manager - ASTSCA