WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL



## **LIEBHERR LH60 096587**

Front Right Wheel Hub

| PETRO CANADA TRAXON 75V   | V90 SYNTH        | ETIC   | ( GAL         | )         |             |          |          |
|---|------------------|--------|---------------|-----------|-------------|----------|----------|
| RECOMMENDATION  | Test             | UOM    | Method        | Limit/Abn | Current     | History1 | History2 |
| Resample at the next service interval to monitor.               | Sample Number    |        | Client Info   |           | LH0284794   |          |          |
| nesample at the next service interval to monitor.               | Sample Date      |        | Client Info   |           | 24 Feb 2024 |          |          |
|   | Machine Age      | hrs    | Client Info   |           | 11676       |          |          |
|   | Oil Age          | hrs    | Client Info   |           | 0           |          |          |
|   | Filter Age       | hrs    | Client Info   |           | 0           |          |          |
|   | Oil Changed      |        | Client Info   |           | Changed     |          |          |
|   | Filter Changed   |        | Client Info   |           | N/A         |          |          |
|   | Sample Status    |        |               |           | NORMAL      |          |          |
| WEAR  | Iron             | ppm    | ASTM D5185(m) | >650      | 244         |          |          |
| All component wear rates are normal.                            | Chromium         | ppm    | ASTM D5185(m) | >4        | 2           |          |          |
|   | Nickel           | ppm    | ASTM D5185(m) | >4        | <1          |          |          |
|   | Titanium         | ppm    | ASTM D5185(m) | >4        | 0           |          |          |
|   | Silver           | ppm    | ASTM D5185(m) |           | 0           |          |          |
|   | Aluminum         | ppm    | ASTM D5185(m) | >25       | 3           |          |          |
|   | Lead             | ppm    | ASTM D5185(m) | >4        | 1           |          |          |
|   | Copper           | ppm    | ASTM D5185(m) | >60       | 52          |          |          |
|   | Tin              | ppm    | ASTM D5185(m) | >4        | 0           |          |          |
|   | Vanadium         | ppm    | ASTM D5185(m) |           | 0           |          |          |
|   | White Metal      | scalar | Visual*       | NONE      | LIGHT       |          |          |
|   | Yellow Metal     | scalar | Visual*       | NONE      | NONE        |          |          |
| CONTAMINATION   | Silicon          | ppm    | ASTM D5185(m) | >75       | 3           |          |          |
| There is no indication of any contamination in the oil.         | Potassium        | ppm    | ASTM D5185(m) | >20       | 2           |          |          |
| There is no indication of any contamination in the oil.         | Water            |        | WC Method     | >0.2      | NEG         |          |          |
|   | Silt             | scalar | Visual*       | NONE      | VLITE       |          |          |
|   | Debris           | scalar | Visual*       | NONE      | NONE        |          |          |
|   | Sand/Dirt        | scalar | Visual*       | NONE      | NONE        |          |          |
|   | Appearance       | scalar | Visual*       | NORML     | NORML       |          |          |
|   | Odor             | scalar | Visual*       | NORML     | NORML       |          |          |
|   | Emulsified Water | scalar | Visual*       | >0.2      | NEG         |          |          |
| FLUID CONDITION   | Sodium           | ppm    | ASTM D5185(m) |           | <1          |          |          |
| The condition of the oil is acceptable for the time in service. | Boron            | ppm    | ASTM D5185(m) | 328       | 102         |          |          |
| · ·   | Barium           | ppm    | ASTM D5185(m) | 1         | 3           |          |          |
|   | Molybdenum       | ppm    | ASTM D5185(m) |           | 0           |          |          |
|   | Manganese        | ppm    | ASTM D5185(m) |           | 3           |          |          |
|   | Magnesium        | ppm    | ASTM D5185(m) |           | <1          |          |          |
|   | Calcium          | ppm    | ASTM D5185(m) |           | 4           |          |          |
|   | Phosphorus       | ppm    | ASTM D5185(m) |           | 834         |          |          |
|   | Zinc             | ppm    | ASTM D5185(m) |           | 38          |          |          |
|   | Sulfur           | ppm    |               | 17909     | 21111       |          |          |
|   | Visc @ 40°C      | cSt    | ASTM D7279(m) | 99.6      | 100         |          |          |





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: LH0284794 Lab Number : 02620013 Unique Number : 5737123 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested** 

Diagnosed

: 05 Mar 2024

: 05 Mar 2024 - Wes Davis

: 05 Mar 2024

CA E1A 3A5 Contact: Service Manager

**American Iron and Metal** 

131 Toombs St

Moncton, NB

T: F:

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.