WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

[19624] Machine Id 3194008156

Port IPS

GEAR OIL SAE 75W90 (17 LTR)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm.	Sample Number		Client Info		VPA056523		
	Sample Date		Client Info		04 Mar 2024		
	Machine Age	hrs	Client Info		1900		
	Oil Age	hrs	Client Info		50		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184*		0		
All component wear rates are normal.	Iron	ppm	ASTM D5185(m)	>200	83		
	Chromium	ppm	ASTM D5185(m)	>10	<1		
	Nickel	ppm	ASTM D5185(m)	>10	1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)		2		
	Lead	ppm	ASTM D5185(m)		<1		
	Copper	ppm	ASTM D5185(m)		4		
	Tin	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)		5		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	1		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor		Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		6		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	272		
	Barium	ppm	ASTM D5185(m)	200	0		
	Molybdenum	ppm	ASTM D5185(m)	12	<1		
	Manganese	ppm	ASTM D5185(m)		<1		
	Magnesium	ppm	ASTM D5185(m)		2		
	Calcium	ppm	ASTM D5185(m)		7		
	Phosphorus	ppm	ASTM D5185(m)		1387		
	Zinc	ppm	. ,	125	10		
	Sulfur	ppm	ASTM D5185(m)		22841		
	Visc @ 40°C	cSt	ASTM D7279(m)	109	105		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No. Lab Number : 02620248

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : VPA056523

Unique Number : 5737358

Received **Tested** Diagnosed

: 06 Mar 2024 : 06 Mar 2024

: 06 Mar 2024 - Kevin Marson

Test Package: MOB 1 (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Sea Power Ltd 2077 Amelia Ave SIDNEY, BC **CA V8L 3Z8** Contact: Kayla Sousa service@seapower.ca T: (250)656-4341