WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL



## **LIEBHERR L580 070558-1762**

Front Left Wheel Hub

LIEBHERR GEAR BASIC 90 LS ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LH0218133	LH0275619	
nesample at the next service interval to monitor.	Sample Date		Client Info		12 Mar 2024	02 Jan 2024	
	Machine Age	hrs	Client Info		1460	797	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185(m)	>500	110	264	
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>8	<1	1	
	Nickel	ppm	ASTM D5185(m)	>5	<1	1	
	Titanium	ppm	ASTM D5185(m)		0	0	
	Silver	ppm	ASTM D5185(m)		0	0	
	Aluminum	ppm	ASTM D5185(m)	>5	<1	2	
	Lead	ppm	ASTM D5185(m)	>5	2	2	
	Copper	ppm	ASTM D5185(m)	>50	84	71	
	Tin	ppm	ASTM D5185(m)		6	12	
	Vanadium	ppm	ASTM D5185(m)		0	0	
	White Metal	scalar	Visual*	NONE	VLITE	NONE	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	8	19	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	<1	1	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	Visual*	NONE	NONE	LIGHT	
	Debris	scalar	Visual*	NONE	VLITE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		3	9	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	0	<1	1	
The condition of the ones acceptable for the time in service.	Barium	ppm	ASTM D5185(m)	0	0	0	
	Molybdenum	ppm	ASTM D5185(m)	0	0	0	
	Manganese	ppm	ASTM D5185(m)	0	20	65	
	Magnesium	ppm	ASTM D5185(m)	<1	1	2	
	Calcium	ppm	ASTM D5185(m)	<1	4	9	
	Phosphorus	ppm	ASTM D5185(m)	2143	2348	2231	
	Zinc	ppm	ASTM D5185(m)	<1	75	149	
	Sulfur	ppm	ASTM D5185(m)	23468	26016	25331	
	Visc @ 40°C	cSt	ASTM D7279(m)	170	180	191	





CALA ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No.

: LH0218133 Lab Number : 02625364

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received

**Tested** Unique Number : 5750483 Diagnosed Test Package : MOBCE ( Additional Tests: Visual )

: 28 Mar 2024 : 28 Mar 2024

: 28 Mar 2024 - Kevin Marson

1012 CHEMIN DE PARC INDUSTRIEL

BOIS-FRANC, QC CA J9E 3A9

**HUBERT ET FILS INC** 

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

T:

F: