**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL ABNORMAL** 

Machine Id

Or1979

## Transmission

PETRO CANADA DURATRAN SYNTHETIC (75	LTR)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor. The fluid was specified as PETRO CANADA DURATRAN SYNTHETIC, however, a fluid match indicates that this fluid is SAE 10W Diesel Engine Oil. Please confirm the fluid type and grade on your next sample. Please specify the component make and model with your next sample.	Sample Number		Client Info		GFL0113385		
	Sample Date		Client Info		01 Apr 2024		
	Machine Age	hrs	Client Info		16204		
	Oil Age	hrs	Client Info		16204		
	Filter Age	hrs	Client Info		16204		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				ABNORMAL		
WEAD							
WEAR	Iron	ppm	ASTM D5185(m)		15		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>10	0		
	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>50	2		
	Lead	ppm	ASTM D5185(m)	>50	3		
	Copper	ppm	ASTM D5185(m)	>200	45		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>50	5		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185(m)		1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	VLITE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		6		
	Boron	ppm	ASTM D5185(m)	112	27		
The fluid viscosity is lower than typical, possibly indicating the addition of lighter grade fluid. This plus the additive levels indicates that this is not the same brand, or type of oil as reported. The condition of the fluid is acceptable for the time in service.	Barium	ppm	ASTM D5185(m)		 <1		
	Molybdenum	ppm	ASTM D5185(m)		1		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		9		
	Calcium	ppm	ASTM D5185(m)	3777	3385		
	Phosphorus	ppm	ASTM D5185(m)	1240	947		
	Zinc	ppm	ASTM D5185(m)	1513	901		
	Sulfur	ppm	ASTM D5185(m)	2716	3166		
	Visc @ 40°C	cSt	ASTM D7279(m)	46.79	<b>△</b> 35.3		
Report Id: GFL720 [WCAMIS] 02626448 (Generated: 04/03/2024 14:00:09) Rev: 1						ed By: Charl	oo Borgorou





CALA ISO 17025:2017 Accredited

Laboratory

Laboratory Sample No.

: GFL0113385 Lab Number : 02626448 Unique Number : 5759580

Test Package : MOB 1

Received **Tested** Diagnosed

: 03 Apr 2024 : 03 Apr 2024

: 03 Apr 2024 - Kevin Marson

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 720 - Lafleche - Landfill 17125 Lafleche Road, Moose Creek, ON CA K0C 1W0 Contact: Charles Bergeron cbergeron@gflenv.com T: (613)538-4853 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.