

#### Machine Id **100023135 CONVERYOR GEARBOX** Component **Gearbox** Fluid

# SHELL OMALA S4 GX 150 (--- GAL)

# RECOMMENDATION

Resample at the next service interval to monitor.

### **WEAR**

All component wear rates are normal.

### CONTAMINATION


There is no indication of any contamination in the oil.


## FLUID CONDITION


The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0922021		
Sample Date		Client Info		02 Apr 2024		
Machine Age	hrs	Client Info		1245		
Oil Age	hrs	Client Info		1245		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
Iron			>200	47		
Chromium	ppm	ASTM D5185(m) ASTM D5185(m)	>200	47 <1		
Nickel	ppm	. ,	>15	0		
Titanium	ppm	ASTM D5185(m)	>10	0		
Silver	ppm	ASTM D5185(m) ASTM D5185(m)		0		
Aluminum	ppm	( )	>25	0 <1		
Lead	ppm	ASTM D5185(m)	>25	<1 0		
	ppm	ASTM D5185(m)		•		
Copper	ppm	ASTM D5185(m)	>200	<1		
Tin	ppm	ASTM D5185(m)	>25	0		
Vanadium	ppm	ASTM D5185(m)	NONE	-		
White Metal	scalar	Visual*		NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Silicon	ppm	ASTM D5185(m)	>50	15		
Silicon Potassium	ppm ppm	ASTM D5185(m) ASTM D5185(m)	>50 >20	15 <1		
				-		
Potassium		ASTM D5185(m)	>20	<1		
Potassium Water	ppm	ASTM D5185(m) WC Method	>20 >0.2	<1 NEG		
Potassium Water Silt	ppm scalar	ASTM D5185(m) WC Method Visual*	>20 >0.2 NONE	<1 NEG NONE		
Potassium Water Silt Debris	ppm scalar scalar	ASTM D5185(m) WC Method Visual* Visual*	>20 >0.2 NONE NONE	<1 NEG NONE VLITE		
Potassium Water Silt Debris Sand/Dirt	ppm scalar scalar scalar	ASTM D5185(m) WC Method Visual* Visual* Visual*	>20 >0.2 NONE NONE NONE	<1 NEG NONE VLITE NONE		   
Potassium Water Silt Debris Sand/Dirt Appearance	ppm scalar scalar scalar scalar	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual*	>20 >0.2 NONE NONE NONE NORML	<1 NEG NONE VLITE NONE NORML	  	   
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water	ppm scalar scalar scalar scalar scalar scalar	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual*	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NONE NORML NORML NEG	  	
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium	ppm scalar scalar scalar scalar scalar scalar	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual*	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NONE NORML NORML NEG		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron	ppm scalar scalar scalar scalar scalar scalar ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORE NORML NEG 2 <1		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium	ppm scalar scalar scalar scalar scalar scalar ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Molybdenum	ppm scalar scalar scalar scalar scalar ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 <1 0		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Malybdenum Manganese	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 0 0 0		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Malybdenum Manganese Magnesium	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 0 0 3		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Malybdenum Manganese Magnesium	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 <1 0 0 3 1204		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Barium Malybdenum Manganese Magnesium Calcium	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 <1 0 0 0 3 1204 480		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 0 0 3 1204 480 4		
Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Barium Malybdenum Manganese Magnesium Calcium	ppm scalar scalar scalar scalar scalar ppm ppm ppm ppm ppm ppm	ASTM D5185(m) WC Method Visual* Visual* Visual* Visual* Visual* ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	>20 >0.2 NONE NONE NORML NORML	<1 NEG NONE VLITE NORML NORML NEG 2 <1 <1 <1 0 0 0 3 1204 480		

Contact/Location: Andre Huter - MOUCOL







Contact/Location: Andre Huter - MOUCOL Page 2 of 2