

OIL ANALYSIS REPORT

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area


(CGYTL) PERIMETER AVIATION [53141]

[CGYTL] FAIRCHILD METRO 23 SA227CC P-44115C (S/N CC829B)

Right Jet Turbine

EASTMAN TURBO OIL 2380 (--- GAL)

DATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		GT57610	GT57426	GT57393
	Sample Date		Client Info		01 Apr 2024	05 Feb 2024	23 Dec 2023
	Machine Age	hrs	Client Info		0	0	0
	Oil Age	hrs	Client Info		764	665	567
	Filter Age	hrs	Client Info		99	98	95
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status					NORMAL	
	Iron	ppm	ASTM D5185(m)	>8	0	<1	<1
	Chromium	ppm	ASTM D5185(m)	>2	0	0	0
	Nickel	ppm	ASTM D5185(m)	>2	0	0	0
	Silver	ppm	ASTM D5185(m)	>2	0	0	0
	Aluminum	ppm	ASTM D5185(m)	>2	<1	<1	<1
	Lead	ppm	ASTM D5185(m)	>3	<1	<1	<1
	Copper	ppm	ASTM D5185(m)	>3	<1	<1	<1
	 Water		WC Method	>0.1	NEG	NEG	NEG
	Magnesium	ppm	ASTM D5185(m)	0	0	0	0
	Acid Number (AN)	mg KOH/g	ASTM D974*	0.43	0.80	0.77	0.75
	Visc @ 40°C	cSt	ASTM D7279(m)	24.2)	24.7	







Laboratory Sample No.

Lab Number : 02626832

: GT57610 Unique Number : 5759964

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received Tested

: 04 Apr 2024 Diagnosed

Honeywell Engines 111 S. 34th Street, 301 Receiving, Attn: SOAP Program

PHOENIX, AZ US 85034 Contact: GARRETT

Test Package : G331 (Additional Tests: ICP) To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

T: F: (602)365-2676