



# LIEBHERR

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**(346464)**  
Machine Id  
**LIEBHERR LH30M 124535-1253**  
Component  
**Rear Differential**  
Fluid  
**GEAR OIL SAE 75W90 (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LH0286586</b>	LH0269637	LH0224215
Sample Date		Client Info		<b>16 Mar 2024</b>	18 Oct 2023	04 Apr 2022
Machine Age	hrs	Client Info		<b>6121</b>	5046	2025
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	N/A
Filter Changed		Client Info		<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>190	<b>3</b>	6	6
Chromium	ppm	ASTM D5185(m)	>2	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m)	>2	<b>0</b>	<1	<1
Titanium	ppm	ASTM D5185(m)		<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)		<b>0</b>	<1	0
Aluminum	ppm	ASTM D5185(m)	>5	<b>0</b>	0	<1
Lead	ppm	ASTM D5185(m)	>15	<b>0</b>	<1	0
Copper	ppm	ASTM D5185(m)	>70	<b>1</b>	4	2
Tin	ppm	ASTM D5185(m)	>2	<b>0</b>	0	<1
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	0	0
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	VLITE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>20	<b>0</b>	1	2
Potassium	ppm	ASTM D5185(m)	>20	<b>&lt;1</b>	0	<1
Water		WC Method	>.2	<b>NEG</b>	NEG	NEG
Silt	scalar	Visual*	NONE	<b>NONE</b>	VLITE	NONE
Debris	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	<b>VLITE</b>	NONE	NONE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>.2	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<b>2</b>	2	3
Boron	ppm	ASTM D5185(m)	400	<b>304</b>	287	282
Barium	ppm	ASTM D5185(m)	200	<b>&lt;1</b>	<1	1
Molybdenum	ppm	ASTM D5185(m)	12	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)		<b>0</b>	0	<1
Magnesium	ppm	ASTM D5185(m)	12	<b>1</b>	1	3
Calcium	ppm	ASTM D5185(m)	150	<b>46</b>	142	617
Phosphorus	ppm	ASTM D5185(m)	1650	<b>1187</b>	1199	1307
Zinc	ppm	ASTM D5185(m)	125	<b>24</b>	68	269
Sulfur	ppm	ASTM D5185(m)	22500	<b>20442</b>	20098	18123
Visc @ 40°C	cSt	ASTM D7279(m)	109	<b>103</b>	98.5	94.3



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : LH0286586 **Received** : 05 Apr 2024  
**Lab Number** : 02627093 **Tested** : 05 Apr 2024  
**Unique Number** : 5760225 **Diagnosed** : 05 Apr 2024 - Wes Davis  
**Test Package** : MOB 1

**JOHN ROSS & SONS LTD.**  
 85 GLASSY AVENUE  
 TRURO, NS  
 CA B2N 6Z1  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

T:  
F: