



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
UPSOURCE CANADA [AU135431]

Machine Id
30370880

Component
Genset

Fluid
VALVOLINE PREMIUM BLUE 2000 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		CU0023078	---	---
Sample Date		Client Info		05 Apr 2024	---	---
Machine Age	hrs	Client Info		871	---	---
Oil Age	hrs	Client Info		19	---	---
Filter Age	hrs	Client Info		19	---	---
Oil Changed		Client Info		Not Changd	---	---
Filter Changed		Client Info		Not Changd	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>50	2	---	---
Chromium	ppm	ASTM D5185(m)	>4	0	---	---
Nickel	ppm	ASTM D5185(m)	>2	0	---	---
Titanium	ppm	ASTM D5185(m)		0	---	---
Silver	ppm	ASTM D5185(m)	>5	0	---	---
Aluminum	ppm	ASTM D5185(m)	>12	<1	---	---
Lead	ppm	ASTM D5185(m)	>17	0	---	---
Copper	ppm	ASTM D5185(m)	>70	5	---	---
Tin	ppm	ASTM D5185(m)	>15	0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	2	---	---
Potassium	ppm	ASTM D5185(m)	>20	0	---	---
Fuel		WC Method	>4.0	<1.0	---	---
Water		WC Method	>0.1	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	ASTM D7844*		0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	6.3	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.8	---	---
Silt	scalar	Visual*	NONE	NONE	---	---
Debris	scalar	Visual*	NONE	VLITE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*	>0.1	NEG	---	---

FLUID CONDITION

The oil viscosity is lower than typical, possibly indicating the addition of lighter grade oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		3	---	---
Boron	ppm	ASTM D5185(m)		43	---	---
Barium	ppm	ASTM D5185(m)		0	---	---
Molybdenum	ppm	ASTM D5185(m)		44	---	---
Manganese	ppm	ASTM D5185(m)		<1	---	---
Magnesium	ppm	ASTM D5185(m)		767	---	---
Calcium	ppm	ASTM D5185(m)		1170	---	---
Phosphorus	ppm	ASTM D5185(m)		723	---	---
Zinc	ppm	ASTM D5185(m)		836	---	---
Sulfur	ppm	ASTM D5185(m)		1981	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	16.4	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	118	98.8	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	15.2	13.5	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	134	136	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : CU0023078 **Received** : 12 Apr 2024
Lab Number : 02628499 **Tested** : 15 Apr 2024
Unique Number : 5761631 **Diagnosed** : 15 Apr 2024 - Kevin Marson
Test Package : MOB 1 (Additional Tests: KV40, VI, Visual)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

CUMMINS DIESEL
 50 SIMMONDS DRIVE
 DARTMOUTH, NS
 CA B3B 1R3
 Contact: STEVE GAETZ
 steve.gaetz@cummins.com
 T: (902)456-7307
 F: (902)468-5177