WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL



Machine Id **VOLVO A30G HDTR0824**

Front Differential

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|---|------------------|--------|-------------------------------|-------------|-------------|----------|----------|
| Resample at the next service interval to monitor. | Sample Number | OOM | Client Info | Little/toll | WC0902318 | | |
| | Sample Date | | Client Info | | 05 Apr 2024 | | |
| | Machine Age | hrs | Client Info | | 26244 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| NEAD. | | | | | | | |
| WEAR | Iron | ppm | ASTM D5185(m) | | 46 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185(m) | | <1 | | |
| | Nickel | ppm | ASTM D5185(m) | >10 | <1 | | |
| | Titanium | ppm | ASTM D5185(m) | | 0 | | |
| | Silver | ppm | ASTM D5185(m) | 00 | 0 | | |
| | Aluminum | ppm | 1 / | >30 | <1 | | |
| | Lead | ppm | ASTM D5185(m) | >50 | 0 | | |
| | Copper | ppm | ASTM D5185(m) | >150 | 5 | | |
| | Tin Vanadium | ppm | . , | >20 | 0 | | |
| | White Metal | ppm | ASTM D5185(m) Visual* | NONE | 0 NONE | | |
| | | scalar | | NONE | NONE | | |
| | Yellow Metal | scalar | Visual* | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185(m) | >50 | 4 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185(m) | >20 | <1 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | Visual* | NONE | NONE | | |
| | Debris | scalar | Visual* | NONE | NONE | | |
| | Sand/Dirt | scalar | Visual* | NONE | VLITE | | |
| | Appearance | scalar | Visual* | NORML | NORML | | |
| | Odor | scalar | Visual* | NORML | NORML | | |
| | Emulsified Water | scalar | Visual* | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | nnm | ASTM D5185(m) | <u> 50</u> | <1 | | |
| | Boron | ppm | ASTM D5185(III) ASTM D5185(m) | 200 | 123 | | |
| The condition of the oil is acceptable for the time in service. | Barium | ppm | ASTM D5185(m) | | 0 | | |
| | Molybdenum | ppm | ASTM D5185(m) | | 0 | | |
| | Manganese | ppm | ASTM D5185(m) | 0 | <1 | | |
| | Magnesium | ppm | ASTM D5185(m) | 0 | 7 | | |
| | Calcium | ppm | ASTM D5185(m) | 20 | 943 | | |
| | Phosphorus | ppm | . , | 1000 | 936 | | |
| | Zinc | ppm | ASTM D5185(m) | 20 | 357 | | |
| | | | ASTM D5185(m) | 22000 | | | |
| | Sulfur | ppm | AO HVI DO LOGILIII | 22000 | 18532 | | |





CALA ISO 17025:2017 Accredited

Laboratory

Laboratory Sample No. Lab Number

Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : WC0902318 : 02628567

Tested Unique Number : 5761699

Received : 12 Apr 2024 Diagnosed

: 12 Apr 2024 : 12 Apr 2024 - Kevin Marson Agnico Eagle Canada

1350 Government Rd. W, MACASSA COMPLEX Kirkland Lake, ON CA P2N 3J1

Contact: Jay Gould

MacassaMobileUGPlanning@agnicoeagle.com T: (705)567-5208

Validity of results and interpretation are based on the sample and information as supplied.