



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MITSUBISHI 2195 NORTH SERVICE - 750
 Component
Diesel Engine
 Fluid
TOTAL FINA RUBIA TIR 7900 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0888823	WC0787133	WC0665521
Sample Date		Client Info		30 Jan 2024	16 Mar 2023	18 Apr 2022
Machine Age	hrs	Client Info		152	128	109
Oil Age	hrs	Client Info		24	0	0
Filter Age	hrs	Client Info		24	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>100	1	2	2
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>4	0	<1	0
Titanium	ppm	ASTM D5185(m)		0	<1	<1
Silver	ppm	ASTM D5185(m)	>3	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	1	2	1
Lead	ppm	ASTM D5185(m)	>40	<1	2	2
Copper	ppm	ASTM D5185(m)	>330	7	10	12
Tin	ppm	ASTM D5185(m)	>15	<1	1	1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	7	6	6
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0	0	0
Nitration	Abs/cm	ASTM D7624*	>20	5.9	6.4	6.0
Sulfation	Abs/.1mm	ASTM D7415*	>30	17.2	18.9	15.8
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		2	2	2
Boron	ppm	ASTM D5185(m)		40	56	43
Barium	ppm	ASTM D5185(m)		<1	0	0
Molybdenum	ppm	ASTM D5185(m)		72	71	53
Manganese	ppm	ASTM D5185(m)		0	<1	<1
Magnesium	ppm	ASTM D5185(m)		440	80	154
Calcium	ppm	ASTM D5185(m)	3290	1748	2211	2149
Phosphorus	ppm	ASTM D5185(m)	1200	1029	1058	1034
Zinc	ppm	ASTM D5185(m)	1400	1154	1113	1078
Sulfur	ppm	ASTM D5185(m)	4000	3028	3175	3055
Oxidation	Abs/.1mm	ASTM D7414*	>25	13.0	11.6	10.9
Visc @ 100°C	cSt	ASTM D7279(m)	15.5	13.5	13.5	12.9



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0888823 **Received** : 15 Apr 2024
Lab Number : 02628726 **Tested** : 15 Apr 2024
Unique Number : 5761858 **Diagnosed** : 15 Apr 2024 - Wes Davis
Test Package : MOB 1

GenWorx Power Systems Inc.
 785 Westney Road, Unit 4
 Ajax, ON
 CA L1S 7G1
 Contact: J Curtis
 jcurtis@genworx.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.