



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
51 WEST RIVER
 Component
Diesel Engine
 Fluid
TOTAL FINA RUBIA TIR 7900 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0888833	WC0787119	WC0665507
Sample Date		Client Info		04 Mar 2024	02 Mar 2023	14 Mar 2022
Machine Age	hrs	Client Info		636	610	586
Oil Age	hrs	Client Info		26	0	0
Filter Age	hrs	Client Info		26	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>90	3	<1	3
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>2	0	0	0
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	2	2	1
Lead	ppm	ASTM D5185(m)	>40	0	0	<1
Copper	ppm	ASTM D5185(m)	>330	2	0	<1
Tin	ppm	ASTM D5185(m)	>15	0	0	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	7	8	4
Potassium	ppm	ASTM D5185(m)	>20	<1	0	1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>6	0	0	0
Nitration	Abs/cm	ASTM D7624*	>20	8.1	7.3	6.5
Sulfation	Abs/.1mm	ASTM D7415*	>30	17.5	20.1	15.5
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		3	2	2
Boron	ppm	ASTM D5185(m)		76	67	65
Barium	ppm	ASTM D5185(m)		<1	0	0
Molybdenum	ppm	ASTM D5185(m)		78	80	9
Manganese	ppm	ASTM D5185(m)		4	0	<1
Magnesium	ppm	ASTM D5185(m)		28	15	39
Calcium	ppm	ASTM D5185(m)	3290	2267	2108	2348
Phosphorus	ppm	ASTM D5185(m)	1200	1041	1016	1012
Zinc	ppm	ASTM D5185(m)	1400	1167	1078	1044
Sulfur	ppm	ASTM D5185(m)	4000	3126	3058	2404
Oxidation	Abs/.1mm	ASTM D7414*	>25	13.9	12.9	12.3
Visc @ 100°C	cSt	ASTM D7279(m)	15.5	14.1	15.0	13.0



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0888833 **Received** : 15 Apr 2024
Lab Number : 02628728 **Tested** : 15 Apr 2024
Unique Number : 5761860 **Diagnosed** : 15 Apr 2024 - Wes Davis
Test Package : MOB 1

GenWorx Power Systems Inc.
 785 Westney Road, Unit 4
 Ajax, ON
 CA L1S 7G1
 Contact: J Curtis
 jcurtis@genworx.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.