WEAR
CONTAMINATION
FLUID CONDITION


NORMAL NORMAL NORMAL



## Machine Id LIEBHERR LH30M 090077

Front Right Wheel Hub

GEAR OIL SAE 75W90 ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LH0276292	LH	
	Sample Date		Client Info		16 Apr 2024	05 Jan 2022	
	Machine Age	hrs	Client Info		6756	5072	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		None	None	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185(m)	>450	15	40	
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>4	0	<1	
	Nickel	ppm	ASTM D5185(m)	>2	0	<1	
	Titanium	ppm	ASTM D5185(m)		0	0	
	Silver	ppm	ASTM D5185(m)		0	<1	
	Aluminum	ppm	ASTM D5185(m)	>15	0	<1	
	Lead	ppm	ASTM D5185(m)	>4	0	<1	
	Copper	ppm	ASTM D5185(m)	>75	2	5	
	Tin	ppm	ASTM D5185(m)		0	0	
	Vanadium	ppm	ASTM D5185(m)		0	0	
	White Metal	scalar	Visual*	NONE	VLITE	VLITE	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>60	0	2	
	Potassium	ppm	ASTM D5185(m)	>20	0	<1	
There is no indication of any contamination in the oil.	Water	PPIII		>0.2	NEG	NEG	
	Silt	scalar	Visual*	NONE	VLITE	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		4	7	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	316	306	
	Barium	ppm	ASTM D5185(m)	200	<1	<1	
	Molybdenum	ppm	ASTM D5185(m)	12	0	0	
	Manganese	ppm	ASTM D5185(m)		0	<1	
	Magnesium	ppm	ASTM D5185(m)		1	3	
	Calcium	ppm	ASTM D5185(m)		36	238	
	Phosphorus	ppm	ASTM D5185(m)		1250	1366	
	Zinc	ppm	ASTM D5185(m)		16	50	
	Sulfur	ppm	, ,	22500	21223	21409	
	Visc @ 40°C	cSt	ASTM D7279(m)	109	102	99.0	





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02629785 Unique Number : 5762917

: LH0276292

Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 17 Apr 2024 **Tested** : 18 Apr 2024

> Diagnosed : 18 Apr 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

**ELG Canada** 4375 CORPORATE DRIVE BURLINGTON, ON CA L7L 5P7

Contact: Service Manager

F: (905)335-9687

Submitted By: Rick Cule