



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[85357]

Machine Id
4331 LAWRENCE ST E T 2ND FLLOR TOP SOUTH CITY OF TORONTO - TORONTO POLICE 790927393

Component
Rear Diesel Engine

Fluid
ESSO XD-3 EXTRA 15W40 (40 LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PN0005852	PN0004680	PN0003347
Sample Date		Client Info		12 Apr 2024	14 Apr 2023	13 Apr 2022
Machine Age	hrs	Client Info		340	319	303
Oil Age	hrs	Client Info		319	17	0
Filter Age	hrs	Client Info		319	17	0
Oil Changed		Client Info		Not Changed	Changed	Changed
Filter Changed		Client Info		Not Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>90	<1	1	1
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>2	<1	0	<1
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	1	2	2
Lead	ppm	ASTM D5185(m)	>40	0	0	<1
Copper	ppm	ASTM D5185(m)	>330	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	2	4	6
Potassium	ppm	ASTM D5185(m)	>20	0	<1	<1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>6	0	0	0
Nitration	Abs/cm	ASTM D7624*	>20	4.4	6.8	7.1
Sulfation	Abs/.1mm	ASTM D7415*	>30	17.8	17.1	19.2
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>192	<1	2	2
Boron	ppm	ASTM D5185(m)		8	72	76
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		61	82	84
Manganese	ppm	ASTM D5185(m)		0	<1	0
Magnesium	ppm	ASTM D5185(m)		883	29	38
Calcium	ppm	ASTM D5185(m)	3780	1147	2201	2140
Phosphorus	ppm	ASTM D5185(m)	1370	1005	1070	1056
Zinc	ppm	ASTM D5185(m)	1500	1155	1105	1169
Sulfur	ppm	ASTM D5185(m)	3800	2648	3217	3283
Oxidation	Abs/.1mm	ASTM D7414*	>25	12.7	12.1	12.8
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	14.7	14.0	14.1



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PN0005852
Lab Number : 02630530
Unique Number : 5763662
Test Package : MOB 1
Received : 22 Apr 2024
Tested : 22 Apr 2024
Diagnosed : 22 Apr 2024 - Wes Davis

POWER STATION INC.
 1050 JAYSON COURT
 MISSISSAUGA, ON
 CA L4W 2V5
 Contact: Brett Kinkley
 Bkinkley@pwrstn.com
 T:
 F: (905)565-8544

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.