WEAR CONTAMINATION FLUID CONDITION

NORMAL

ABNORMAL

NORMAL



[5480] Machine Id 352150 Component Drop Box

GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDAT	

We advise that you check all areas where dirt can enter the system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.

				/		
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP392994		
Sample Date		Client Info		15 Apr 2024		
Machine Age	hrs	Client Info		5936		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				ABNORMAL		
Iron	ppm	ASTM D5185(m)	>500	211		
11011	ppiii	NOTIVI DOTOS(III)	>500	211		
Chromium	mag	ASTM D5185(m)	>20	3		

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>500	211	
Chromium	ppm	ASTM D5185(m)	>20	3	
Nickel	ppm	ASTM D5185(m)	>10	<1	
Titanium	ppm	ASTM D5185(m)		<1	
Silver	ppm	ASTM D5185(m)		0	
Aluminum	ppm	ASTM D5185(m)	>30	8	
Lead	ppm	ASTM D5185(m)	>30	0	
Copper	ppm	ASTM D5185(m)	>30	8	
Tin	ppm	ASTM D5185(m)	>20	0	
Vanadium	ppm	ASTM D5185(m)		0	
White Metal	scalar	Visual*	NONE	NONE	
Yellow Metal	scalar	Visual*	NONE	NONE	
		40TH B=40=4			
Silicon	ppm	ASTM D5185(m)	>50	<u> </u>	
Potassium	mag	ASTM D5185(m)	>20	1	

CONTAMINATION

There is a moderate concentration of dirt present in the oil.

Silicon	ppm	ASTM D5185(m)	>50	<u> </u>	
Potassium	ppm	ASTM D5185(m)	>20	1	
Water		WC Method	>0.2	NEG	
Silt	scalar	Visual*	NONE	NONE	
Debris	scalar	Visual*	NONE	NONE	
Sand/Dirt	scalar	Visual*	NONE	NONE	
Appearance	scalar	Visual*	NORML	NORML	
Odor	scalar	Visual*	NORML	NORML	
Emulsified Water	scalar	Visual*	>0.2	NEG	
		40TH DE (05)			
Sodium	ppm	ASTM D5185(m)	>170	2	
Boron	ppm	ASTM D5185(m)	400	142	

FLUID CONDITION

The oil is no longer serviceable due to the presence of contaminants.

Odor	scalar	visuai	NORIVIL	NORML	
Emulsified Water	scalar	Visual*	>0.2	NEG	
Sodium	ppm	ASTM D5185(m)	>170	2	
Boron	ppm	ASTM D5185(m)	400	142	
Barium	ppm	ASTM D5185(m)	200	<1	
Molybdenum	ppm	ASTM D5185(m)	12	12	
Manganese	ppm	ASTM D5185(m)		4	
Magnesium	ppm	ASTM D5185(m)	12	3	
Calcium	ppm	ASTM D5185(m)	150	23	
Phosphorus	ppm	ASTM D5185(m)	1650	1035	
Zinc	ppm	ASTM D5185(m)	125	33	
Sulfur	ppm	ASTM D5185(m)	22500	23898	
Visc @ 40°C	cSt	ASTM D7279(m)	143	125	
		_			





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: VCP392994 Lab Number : 02630711 Unique Number : 5763843 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 22 Apr 2024 **Tested** : 22 Apr 2024

Diagnosed

: 22 Apr 2024 - Kevin Marson

GREAT WEST EQUIPMENT 1600 KOSMINA ROAD, 123 L&A CROSS RD VERNON, BC

CA V1T 8T2 Contact: Sarah Lawrence slawrence@gwequipment.com

> T: (866)627-2357 F: (250)549-3397

Validity of results and interpretation are based on the sample and information as supplied.