



Machine Id
727009
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0113246	GFL0097314	GFL0097333
Sample Date		Client Info		18 Apr 2024	11 Jan 2024	04 Jan 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		40759	17390	17354
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>120	9	58	5
Chromium	ppm	ASTM D5185(m)	>20	0	2	0
Nickel	ppm	ASTM D5185(m)	>5	0	<1	<1
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	<1	0
Aluminum	ppm	ASTM D5185(m)	>20	1	24	2
Lead	ppm	ASTM D5185(m)	>40	0	5	<1
Copper	ppm	ASTM D5185(m)	>330	<1	20	1
Tin	ppm	ASTM D5185(m)	>15	0	3	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	<1	▲ 43	4
Potassium	ppm	ASTM D5185(m)	>20	0	70	1
Fuel		WC Method	>3.0	<1.0	1.1	2.3
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>4	1.7	0.1	0.2
Nitration	Abs/cm	ASTM D7624*	>20	7.1	9.8	9.1
Sulfation	Abs/.1mm	ASTM D7415*	>30	20.9	22.6	22.3
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		1	6	2
Boron	ppm	ASTM D5185(m)	0	8	33	30
Barium	ppm	ASTM D5185(m)	0	0	5	0
Molybdenum	ppm	ASTM D5185(m)	60	53	13	40
Manganese	ppm	ASTM D5185(m)	0	0	6	0
Magnesium	ppm	ASTM D5185(m)	1010	845	731	489
Calcium	ppm	ASTM D5185(m)	1070	1020	1298	1687
Phosphorus	ppm	ASTM D5185(m)	1150	885	693	706
Zinc	ppm	ASTM D5185(m)	1270	1037	761	852
Sulfur	ppm	ASTM D5185(m)	2060	2291	2411	2046
Oxidation	Abs/.1mm	ASTM D7414*	>25	13.6	19.1	21.6
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	13.3	▲ 11.4	▲ 11.2



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0113246
Lab Number : 02630880
Unique Number : 5772033
Test Package : MOB 1

GFL Environmental - 246 - Windsor
 2700 Deziel Dr
 Windsor, ON
 CA N8W 5H8
 Contact: Dave Varga
 dvarga@gflenv.com
 T: (519)944-8009
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.