
WEAR CONTAMINATION **FLUID CONDITION** **NORMAL NORMAL NORMAL**


Machine Id


REDUCTION GEAR STARBOARD


Component
Starboard Gearbox

CASTROL HYSPIN AWS HYDRAULIC 100 (1200 LTR)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please contact your representative for information regarding the proper sampling kits for your service. NOTE: We recommend using MAR 2 test kits, this testkit includes AN to determine the suitability of the oil for continued use.	Sample Number		Client Info		WC0902416	WC0773495	WC
	Sample Date		Client Info		08 Apr 2024	06 Oct 2023	09 Mar 2023
	Machine Age	hrs	Client Info		40394	28163	25342
	Oil Age	hrs	Client Info		0	0	0
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185(m)	>200	0	0	<1
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>10	0	0	0
	Nickel	ppm	ASTM D5185(m)	>10	0	<1	<1
	Titanium	ppm	ASTM D5185(m)		0	0	0
	Silver	ppm	ASTM D5185(m)		0	<1	<1
	Aluminum	ppm	ASTM D5185(m)	>25	0	0	0
	Lead	ppm	ASTM D5185(m)	>50	2	3	1
	Copper	ppm	ASTM D5185(m)	>200	22	22	12
	Tin	ppm	\ /	>10	0	<1	<1
	Vanadium	ppm	ASTM D5185(m)		0	0	0
	White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>50	0	<1	<1
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	0	0	0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	Visual*	NONE	NONE	NONE	NONE
	Debris	scalar	Visual*	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
	Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
	Odor	scalar	Visual*	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		0	<1	0
The condition of the oil is acceptable for the time in service (unconfirmed).	Boron	ppm	ASTM D5185(m)		<1	<1	<1
	Barium	ppm	ASTM D5185(m)		0	0	0
	Molybdenum	ppm	ASTM D5185(m)		0	0	0
	Manganese	ppm	ASTM D5185(m)		0	0	0
	Magnesium	ppm	ASTM D5185(m)		<1	0	0
	Calcium	ppm	ASTM D5185(m)		46	47	49
	Phosphorus	ppm	ASTM D5185(m)		386	391	435
	Zinc	ppm	ASTM D5185(m)		480	489	484
	Sulfur	ppm	ASTM D5185(m)		4998	5189	5413
Papart Id: UODIZONADO IMCAMIS) 02620061 (Canavatad: 0.4/22/2024 15:47:57) Day: 1	Visc @ 40°C	cSt	ASTM D7279(m)	103.6	91.5	92.2	94.0











CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WC0902416 Lab Number : 02630951

Unique Number : 5772104 Test Package : MAR 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested**

Diagnosed

: 23 Apr 2024 : 23 Apr 2024 : 23 Apr 2024 - Wes Davis

Horizon Maritime Services Ltd. - Horizon Arctic 87 WATER STREET,, 2ND FLOOR ST.JOHNS, NL

CA A1C 1A5 Contact: Horizon Arctic Chief Engineer

chiefeng.arctic@horizonvessel.com T: (709)702-4447

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.