
WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

[33504] CA4400-32987

Unknown Component

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		PP		
	Sample Date		Client Info		24 Apr 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	White Metal	scalar	Visual*	NONE	NONE		
{not applicable}	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Water		WC Method		NEG		
ISO Cleanliness Code (ISO 4406:1999): 20/18/13; Cumulative particle counts >4 μ m = 8762, >6 μ m = 2202, >14 μ m = 53, >21 μ m = 10, >38 μ m = 1, >71 μ m = 0.	Particles >4µm		ASTM D7647	>5000	8762		
	Particles >6µm		ASTM D7647	>1300	2202		
	Particles >14μm		ASTM D7647	>160	53		
	Particles >21µm		ASTM D7647	>40	10		
	Particles >38μm		ASTM D7647	>10	1		
	Particles >71μm		ASTM D7647	>3	0		
	Oil Cleanliness		ISO 4406 (c)	>19/17/14	20/18/13		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		





ISO 17025:2017
Accredited
Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9

 Sample No.
 : PP
 Received
 : 25 Apr 2024

 Lab Number
 : 02631455
 Tested
 : 25 Apr 2024

 Unique Number
 : 5772608
 Diagnosed
 : 25 Apr 2024 - Kevin Marson

Test Package : TEST (Additional Tests: PrtCount)

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

WAKEFIELD CANADA INC.

3620 LAKESHORE BLVD WEST TORONTO, ON CA M8W 1P2 Contact: Tony Fallico tfallico@wakefieldcanada.ca

T: (416)252-5511