



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	ABNORMAL

Area
QC Engine
Machine Id
QC230725MOB2
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0925454	WC0925453	WC0925452
Sample Date		Client Info		26 Apr 2024	25 Apr 2024	24 Apr 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>100	19	19	19
Chromium	ppm	ASTM D5185(m)	>20	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>4	0	0	0
Titanium	ppm	ASTM D5185(m)		3	3	3
Silver	ppm	ASTM D5185(m)	>3	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	4	4	4
Lead	ppm	ASTM D5185(m)	>40	<1	<1	<1
Copper	ppm	ASTM D5185(m)	>330	9	9	9
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION














Light fuel dilution occurring. There is a trace of moisture present in the oil. No other contaminants were detected in the oil.

Silicon	ppm	ASTM D5185(m)	>25	5	5	5
Potassium	ppm	ASTM D5185(m)	>20	▲ 14	▲ 14	▲ 16
Fuel	%	ASTM D7593*	>5	▲ 4.9	▲ 6	▲ 4.9
Water	%	ASTM D6304*	>0.2	▲ 0.198	▲ 0.169	▲ 0.162
ppm Water	ppm	ASTM D6304*	>2000	▲ 1984	▲ 1695	▲ 1626
Glycol	%	ASTM D7922*		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0.3	0.3	0.3
Nitration	Abs/cm	ASTM D7624*	>20	9.9	9.9	9.8
Sulfation	Abs/.1mm	ASTM D7415*	>30	20.8	20.7	20.7
Emulsified Water	scalar	Visual*	>0.2	▲ .2%	▲ .2%	▲ .2%

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. Viscosity of sample indicates oil is within SAE 10W30 range, advise investigate.

Sodium	ppm	ASTM D5185(m)	>216	● 62	● 62	● 63
Boron	ppm	ASTM D5185(m)	250	33	33	37
Barium	ppm	ASTM D5185(m)	10	<1	<1	<1
Molybdenum	ppm	ASTM D5185(m)	100	46	46	46
Manganese	ppm	ASTM D5185(m)		<1	<1	<1
Magnesium	ppm	ASTM D5185(m)	450	614	621	612
Calcium	ppm	ASTM D5185(m)	3000	1492	1484	1472
Phosphorus	ppm	ASTM D5185(m)	1150	844	853	833
Zinc	ppm	ASTM D5185(m)	1350	1013	1016	993
Sulfur	ppm	ASTM D5185(m)	4250	2567	2550	2565
Oxidation	Abs/.1mm	ASTM D7414*	>25	16.1	16.1	16.2
Base Number (BN)	mg KOH/g	ASTM D2896*	8.5	9.15	9.60	8.77
Visc @ 40°C	cSt	ASTM D7279(m)	138	▲ 75.2	▲ 75.0	▲ 75.3
Visc @ 100°C	cSt	ASTM D7279(m)	14.4	▲ 11.3	▲ 11.3	▲ 11.3
Viscosity Index (VI)	Scale	ASTM D2270*	102	141	142	141



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0925454 **Received** : 26 Apr 2024
Lab Number : 02631464 **Tested** : 29 Apr 2024
Unique Number : 5772617 **Diagnosed** : 29 Apr 2024 - Kevin Marson
Test Package : MOB 2 (Additional Tests: Glycol, KF, KV40, PercentFuel, VI)

WearCheck Quality Control Sample Results

Burlington, ON
 CA
 Contact: Dorian Anderson
 dorian.anderson@wearcheck.com
 T: (289)291-4652
 F: (905)569-8605