



# LIEBHERR

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**LIEBHERR LH50M 123311-1216**  
Component  
**Rear Right Wheel Hub**  
Fluid  
**GEAR OIL SAE 75W90 (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LH0289490</b>	LH0261376	LH0242488
Sample Date		Client Info		<b>25 Apr 2024</b>	01 May 2023	24 Oct 2022
Machine Age	hrs	Client Info		<b>8175</b>	6153	5011
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>None</b>	None	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>325	<b>13</b>	10	6
Chromium	ppm	ASTM D5185(m)	>3	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m)	>2	<b>0</b>	0	<1
Titanium	ppm	ASTM D5185(m)	>4	<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185(m)	>10	<b>&lt;1</b>	<1	<1
Lead	ppm	ASTM D5185(m)	>3	<b>0</b>	<1	<1
Copper	ppm	ASTM D5185(m)	>70	<b>14</b>	9	8
Tin	ppm	ASTM D5185(m)	>2	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	0	0
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>70	<b>&lt;1</b>	2	2
Potassium	ppm	ASTM D5185(m)	>20	<b>&lt;1</b>	0	<1
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Silt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	LIGHT	NONE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<b>&lt;1</b>	<1	<1
Boron	ppm	ASTM D5185(m)	400	<b>303</b>	311	305
Barium	ppm	ASTM D5185(m)	200	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185(m)	12	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)		<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185(m)	12	<b>1</b>	2	<1
Calcium	ppm	ASTM D5185(m)	150	<b>13</b>	9	10
Phosphorus	ppm	ASTM D5185(m)	1650	<b>1210</b>	1346	1344
Zinc	ppm	ASTM D5185(m)	125	<b>16</b>	17	14
Sulfur	ppm	ASTM D5185(m)	22500	<b>20051</b>	21325	21704
Visc @ 40°C	cSt	ASTM D7279(m)	109	<b>104</b>	98.7	104



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : LH0289490  
**Lab Number** : 02631730  
**Unique Number** : 5772883  
**Test Package** : MOB 1  
**Received** : 26 Apr 2024  
**Tested** : 26 Apr 2024  
**Diagnosed** : 26 Apr 2024 - Wes Davis

**LONDON SALVAGE & TRADING LTD.**  
 333 EGERTON ST  
 LONDON, ON  
 CA N5Z 2H3  
 Contact: SERVICE MANAGER  
 terry@londonsalvage.com  
 T: (519)451-0680  
 F: (519)659-3576

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.