WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



Machine Id **LIEBHERR LH60M 143695-1475**

Front Differential

LIEBHERR GEAR BASIC 90 LS	(GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LH0248604		
Resample at the next service interval to monitor.	Sample Date		Client Info		19 Apr 2024		
	Machine Age	hrs	Client Info		1001		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>150	7		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m)		<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>5	0		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)	>125	3		
	Tin	ppm	ASTM D5185(m)	>5	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	0		40TM DE (05/)				
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>20	0		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)		<1 NEO		
	Water	cooler	WC Method	>0.2	NEG NONE		
	Debris	scalar	Visual*	NONE			
	Sand/Dirt	scalar scalar	Visual* Visual*	NONE	NONE NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water		Visual*	>0.2	NEG		
ELUID CONDITION			4074.054.054.0				
FLUID CONDITION	Sodium Boron	ppm	ASTM D5185(m) ASTM D5185(m)	0	2 1		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185(III) ASTM D5185(m)		7		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		<1		
	Calcium	ppm	ASTM D5185(m)		6		
	Phosphorus	ppm	ASTM D5185(m)		2290		
	Zinc	ppm	ASTM D5185(m)		4		
	Sulfur	ppm	ASTM D5185(m)		26872		
	Visc @ 40°C	cSt	ASTM D7279(m)		177		
Report Id: GRO21SALIWCAMISI 02631735 (Generated: 04/26/2024 16:36:11) Rev: 1	<u> </u>	-	- (- 7	-		Suh	mitted Bv· ?





CALA ISO 17025:2017 Accredited Laboratory

Sample No.

Laboratory

: LH0248604 Lab Number : 02631735 Unique Number : 5772888 Test Package : MOBCE

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 26 Apr 2024 **Tested**

Diagnosed

: 26 Apr 2024 : 26 Apr 2024 - Wes Davis

Contact: Service Manager

Saint-Michel-de-Squatec, QC

T: F:

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Groupe Lebel Inc

21 rue St-Joseph

CA G0L 4H0