WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

[13980636]

CGB519119

2 Gearbox

MOBIL SHC 630 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.	Sample Number		Client Info		PP		
	Sample Date		Client Info		14 Apr 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184*				
WEAR	Iron	nnm		> 200	0 <1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m) ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)	>10	0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>25	0		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)		<1		
	Tin	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)	720	0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.							
	Silicon	ppm	ASTM D5185(m)	>50	16		
	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water		WC Method		NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185(m)		<1		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		0		
	Calcium	ppm	ASTM D5185(m)		<1		
	Phosphorus	ppm	ASTM D5185(m)		359		
	Zinc	ppm	ASTM D5185(m)		2		
	Sulfur	ppm	ASTM D5185(m)		167		
	Acid Number (AN)	mg KOH/g	ASTM D974*		0.35		
	10 0 1000	0.	A OTA A DEGREE	0.4 = =			

Visc @ 40°C cSt

ASTM D7279(m) 217.7





CALA ISO 17025:2017 Accredited Laboratory

Lab Number

Laboratory Sample No.

: PP : 02631753 Unique Number : 5772906

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested**

: 26 Apr 2024 Diagnosed Test Package : MAR 2 (Additional Tests: TAN Man)

: 26 Apr 2024 : 26 Apr 2024 - Wes Davis

Contact: Reg Costello Hebron.MaintSuperintendent@kcadeutag.com T: (709)778-6228

KCA Deutag Drilling Canada Inc.

Suite 201, 45 Hebron Way

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

St. John's, NL

CA A1A 0P9

F: (709)730-1834