


## NORMAL WEAR NORMAL CONTAMINATION **FLUID CONDITION** NORMAL


## Machine Id 801146 Component Diesel Engine SAE 15W40 (--- GAL)


SAE 15W40 ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		GFL0096774		
	Sample Date		Client Info		15 Apr 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		600		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>80	8		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		<1		
	Nickel	ppm	ASTM D5185(m)		<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm		>3	0		
	Aluminum	ppm	ASTM D5185(m)	>30	1		
	Lead	ppm	ASTM D5185(m)	>30	0		
	Copper	ppm	ASTM D5185(m)	>150	8		
	Tin	ppm	ASTM D5185(m)	>5	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>20	2		
CONTAMINATION	Potassium	ppm		>20	2		
There is no indication of any contamination in the oil.	Fuel	ppiii	. ,	>5	- <1.0		
	Water		WC Method		NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*	>3	0		
	Nitration	Abs/cm	ASTM D7624*	>20	11.7		
	Sulfation	Abs/.1mm	ASTM D7415*	>30	23.9		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>57	7		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		11		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		53		
	Manganese	ppm	ASTM D5185(m)		<1		
	Magnesium	ppm	ASTM D5185(m)		557		
	Calcium	ppm	ASTM D5185(m)		1660		
	Phosphorus	ppm	ASTM D5185(m)		686		
	Zinc	ppm	ASTM D5185(m)		930		
	Sulfur	ppm	ASTM D5185(m)		2034		
	Oxidation	Abs/.1mm	ASTM D7414*	>25	19.6		

Visc @ 100°C cSt ASTM D7279(m) 14.5

14.6







Contact/Location: Sanjay Kisun - GFL574 Page 2 of 2