



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[1269672]
 Machine Id
5544
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0110684	GFL0102712	GFL0082958
Sample Date		Client Info		01 May 2024	08 Jan 2024	05 Jul 2023
Machine Age	hrs	Client Info		10824	10297	9123
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>120	15	15	14
Chromium	ppm	ASTM D5185(m)	>20	0	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	2	4	2
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	4	4	3
Lead	ppm	ASTM D5185(m)	>40	<1	2	2
Copper	ppm	ASTM D5185(m)	>330	2	2	2
Tin	ppm	ASTM D5185(m)	>15	0	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	2	4	5
Potassium	ppm	ASTM D5185(m)	>20	2	2	<1
Fuel		WC Method	>3.0	<1.0	2.7	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>4	0.2	0.3	0.2
Nitration	Abs/cm	ASTM D7624*	>20	8.8	9.6	9.0
Sulfation	Abs/.1mm	ASTM D7415*	>30	18.8	19.6	19.7
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		3	3	2
Boron	ppm	ASTM D5185(m)	0	3	2	3
Barium	ppm	ASTM D5185(m)	0	0	0	0
Molybdenum	ppm	ASTM D5185(m)	60	58	56	59
Manganese	ppm	ASTM D5185(m)	0	<1	0	<1
Magnesium	ppm	ASTM D5185(m)	1010	954	912	949
Calcium	ppm	ASTM D5185(m)	1070	1017	1028	1047
Phosphorus	ppm	ASTM D5185(m)	1150	975	961	1069
Zinc	ppm	ASTM D5185(m)	1270	1152	1146	1165
Sulfur	ppm	ASTM D5185(m)	2060	2494	2601	2507
Oxidation	Abs/.1mm	ASTM D7414*	>25	15.3	16.0	16.7
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	13.1	12.6	13.0



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0110684
Lab Number : 02632973
Unique Number : 5774126
Test Package : MOB 1

GFL Environmental - 207 - Pickering SW
 1034 TOY AVENUE, PICKERING YARD
 PICKERING, ON
 CA L1W 3P1
 Contact: Ian Patton
 ipatton@gflenv.com
 T: (905)831-6297
 F: (905)426-3577

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.