



POWER SYSTEMS
SYSTÈMES DE PUISSANCE

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
SOUTHLAKE HOSPITAL [273409]

Machine Id
DDC 5362004402

Component
Diesel Engine

Fluid
CASTROL 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WA0020684	WA0019560	WA0018123
Sample Date		Client Info		30 Apr 2024	27 Apr 2023	15 Jun 2022
Machine Age	hrs	Client Info		758	718	684
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>100	3	4	5
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>4	0	<1	0
Titanium	ppm	ASTM D5185(m)		0	<1	<1
Silver	ppm	ASTM D5185(m)	>3	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	<1	1	1
Lead	ppm	ASTM D5185(m)	>40	0	<1	<1
Copper	ppm	ASTM D5185(m)	>330	<1	1	1
Tin	ppm	ASTM D5185(m)	>15	0	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	2	4	7
Potassium	ppm	ASTM D5185(m)	>20	1	1	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0	0	0.1
Nitration	Abs/cm	ASTM D7624*	>20	5.6	5.6	6.1
Sulfation	Abs/.1mm	ASTM D7415*	>30	15.9	16.0	18.6
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>406	1	2	2
Boron	ppm	ASTM D5185(m)		5	3	3
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		1	1	2
Manganese	ppm	ASTM D5185(m)		0	<1	<1
Magnesium	ppm	ASTM D5185(m)		41	19	32
Calcium	ppm	ASTM D5185(m)		2415	2447	2319
Phosphorus	ppm	ASTM D5185(m)		939	985	896
Zinc	ppm	ASTM D5185(m)		1057	1031	1018
Sulfur	ppm	ASTM D5185(m)		3166	3238	3143
Oxidation	Abs/.1mm	ASTM D7414*	>25	8.9	8.8	9.2
Visc @ 100°C	cSt	ASTM D7279(m)		13.6	13.8	14.2



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WA0020684 **Received** : 06 May 2024
Lab Number : 02633730 **Tested** : 06 May 2024
Unique Number : 5774883 **Diagnosed** : 06 May 2024 - Wes Davis
Test Package : MOB 1

Wajax Power Systems
 10 Diesel Drive
 Toronto, ON
 CA M8W 2T8
 Contact: David Gilkes
 dgilkes@wajax.com
 T: (416)259-3281
 F: (416)251-6191

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.