WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



Machine Id LIEBHERR L506 55808

Front Differential

LIEBHERR GEAR BASIC 90 LS	(6 LTR)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.	Sample Number		Client Info		LH0282600		
	Sample Date		Client Info		07 May 2024		
	Machine Age	hrs	Client Info		447		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>1250	164		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>6	2		
	Nickel	ppm	ASTM D5185(m)	>4	<1		
	Titanium	ppm	ASTM D5185(m)		<1		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>35	2		
	Lead	ppm	ASTM D5185(m)	>4	0		
	Copper	ppm	ASTM D5185(m)	>30	<1		
	Tin	ppm	ASTM D5185(m)	>4	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>100	7		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)		3		
	Water		WC Method	>.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		10		
Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	0	2		
	Barium	ppm	ASTM D5185(m)	0	5		
	Molybdenum	ppm	ASTM D5185(m)	0	0		
	Manganese	ppm	ASTM D5185(m)	0	7		
	Magnesium	ppm	ASTM D5185(m)	<1	4		
	Calcium	ppm	ASTM D5185(m)	<1	33		
	Phosphorus	ppm	ASTM D5185(m)		2322		
	Zinc	ppm	ASTM D5185(m)		35		
	Sulfur	ppm	ASTM D5185(m)		25392		
Papart Id. POL CTA (IMCAMIC) 02624200 (Caparated: 05/00/2024 12:50:20) Pays 1	Visc @ 40°C	cSt	ASTM D7279(m)		192	ioo Managar	POLETA





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : LH0282600 Lab Number : 02634399 Unique Number : 5775552 Test Package : MOB 1

Received **Tested**

: 09 May 2024 Diagnosed

: 09 May 2024 - Wes Davis

: 09 May 2024

Polyexcave Inc. 787 Ch. Du Moine St-Anne de Sorel, QC CA J3P 5N3

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

T:

F: