WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL



Machine Id LIEBHERR R926K-LC 56729 Component

Left Final Drive

LIEBHERR GEAR BASIC 90 LS	(GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.	Sample Number	OOW	Client Info	LITTIONOTI	LH		
	Sample Date		Client Info		06 May 2024		
	Machine Age	hrs	Client Info		512		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	313		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>10	5		
	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		<1		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>25	10		
	Lead	ppm	ASTM D5185(m)	>25	0		
	Copper	ppm	ASTM D5185(m)	>50	<1		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>75	23		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)		9		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		8		
Additive levels indicate the addition of a different brand, or type of oil.	Boron	ppm	ASTM D5185(m)	0	5		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185(m)	0	22		
	Molybdenum	ppm	ASTM D5185(m)	0	0		
	Manganese	ppm	ASTM D5185(m)	0	4		
	Magnesium	ppm	ASTM D5185(m)	<1	3		
	Calcium	ppm	ASTM D5185(m)	<1	32		
	Phosphorus	ppm	ASTM D5185(m)	2143	1203		
	Zinc	ppm	ASTM D5185(m)	<1	23		
	Sulfur	ppm	ASTM D5185(m)		24740		
Report Id: ROLBALIWCAMISI 02634668 (Generated: 05/10/2024 15:48:38) Rev: 1	Visc @ 40°C	cSt	ASTM D7279(m)	170	202	nitted Bv: Bi	





CALA ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Sample No. : LH

Lab Number : 02634668 Unique Number : 5775821

Received : 10 May 2024 **Tested** : 10 May 2024 Diagnosed : 10 May 2024 - Wes Davis

Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

ROLAND MUNGER

2665 AVENUE DU LABRADOR BAIE COMEAU, QC CA G4Z 3B9

Contact: Roland Munger

T: (661)015-6791 F: