WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



Machine Id LIEBHERR L556 051594

Unknown Component							
LIEBHERR GEAR BASIC 90 LS							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. Resample at the next service interval to monitor. Please provide more complete information on your next sample.	Sample Number		Client Info		LH		
	Sample Date		Client Info		09 May 2024		
	Machine Age	hrs	Client Info		20000		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185(m)		15		
	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)		<1		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)		5		
	Tin	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)		<1		
There is no indication of any contamination in the sample.	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water	pp	WC Method	, =0	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		2		
The condition of the sample is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	0	<1		
	Barium	ppm	ASTM D5185(m)	0	0		
	Molybdenum	ppm	ASTM D5185(m)	0	0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	<1	<1		
	Calcium	ppm	ASTM D5185(m)		2		
	Phosphorus	ppm	ASTM D5185(m)		2221		
	Zinc	ppm	ASTM D5185(m)		4		
	Sulfur	ppm	ASTM D5185(m)	23468	24889		

Visc @ 40°C

183

ASTM D7279(m) 170





CALA ISO 17025:2017 Accredited Laboratory

Sample No.

Laboratory

: LH Lab Number : 02634682 Unique Number : 5775835 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 10 May 2024 **Tested** : 10 May 2024 Diagnosed

: 10 May 2024 - Kevin Marson

PF Resolu Canada Inc. 9 Ch. De la Scierie Baie-Comeau, QC CA G5C 2S9

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

T: F: